

## International Comparison of Standards

Werkstoff Material No.	Germany DIN	U.S.A. AISI / SAE / ASTM	France AFNOR	Great Britain B.S.	Italy UNI	Japan JIS
1.0028	Ust 34 - 2 (SG1T)	-	A 34 - 2	-	Fe 330 Fe 330 B FU	SS 330
1.0034	RSt 34 - 2 (SG2T)	-	A 34 - 2 NE	1449 34/20 HIR.HS.CR.CS	Fe 330 B FN	-
1.0035	S185 (Fe 310 - 0) St 33	A 283 Gr. A	A 33	Fe 310 - 0 1449 15 HR.HS	Fe 320	-
1.0036	S235JRG1 (Fe 360 B) Ust 37 - 2	A 283 Gr. C A 570 Gr.33. 36	-	Fe 360 B 4360 - 40 B	Fe 360 B FU	-
1.0037	235JR (Fe 360 B) St 37 - 2	1015 A 283 Gr. C	E 24 - 2	Fe 360 B 1443 37 / 23 HR Fe 360 B FU 1449 27 / 23 CR	Fe 360 B / C / D	STKM 12 A / C
1.0038	S275JR (Fe 360 B) RSt 37 - 2	A 520 Gr.33. 36	E 24 - 2 NE	Fe 360 B FU 1449 27 / 23 CR 4360 - 40 B	Fe 360 B FN	-
1.0044	S275JR (Fe 430 B) St 44 - 2	1020 A 570 Gr. 40 A 572 Gr. 42	E 28 - 2	Fe 430 B FN 1449 43 / 25 HR.HS 4360 - 43 B	Fe 430 B Fe 430 B FN	SM 400 A / B / C
1.0045	S355JR	-	E 36 - 2	4360 50 B	Fe 510 B	-
1.0050	E295 (Fe 430 B) St 50 - 2	A 570 Gr. 50 A 572 Gr. 50	A 50 - 2	Fe 490 - 2 FN 4360 - 50 B	Fe 490	SS 490
1.0060	ZE335 (Fe 590 2) St 60 - 2	A 572 Gr. 65	A 60 - 2	Fe 590 - 2 FN 4360 - 55 E / 55 C	Fe 60 - 2 Fe 590	SM 570
1.0070	E360 (Fe 690 2) St 70 - 2	-	A 70 - 2	Fe 690 - 2 - FN	Fe 70 - 2 Fe 690	-
1.0112	P 235 S	-	A37AP	1501 - 164 - 360 B LT20	Fe 360 C	-
1.0114	S235JO / St37 - 3 U	-	E24 - 3	4360 - 40 C	Fe 360 C	-
1.0116	S235J2G3 (Fe 360 D 1) St 37 - 2	A 284 Gr.D A 573 Gr. 58 A 573 Ghr. 36 / C A 611 Gr. C	E24 - 3 E24 - 4	Fe 360 D1 FF 1449 37 / 23 CR 4360 - 40 D	Fe 360 C / D Fe 360 C / FN Fe 360 D FF Fe 37 - 2	-
1.0130	P265S	-	A42AP	1501 - 164 - 400B LT 20	-	-
1.0143	S270JO / St 44 - 3 U	A 572 Gr. 42	E28 - 3	4360 - 43C	Fe 430 D	-
1.0144	S270J2G3 (Fe 430 D 1) St 44 - 3	A 573 Gr. 70 A 611 Gr. D A 572 Gr. 42	E28 - 3 E28 - 4	Fe 430 D1 FF 4360 - 43C / 43 D	Fe 430 B Fe 430 C (FN) Fe 430 D (FF)	SM 400 A / B / C
1.0149	S270JOH; RoSt 44 - 2	-	-	4360 - 43 C	Fe 430 C	-
1.0226	DX51D / St 02 Z	-	GC	Z2	FeP 02 G	-
1.0330	DC 01 St 2 / St 12	A 366 (1012) 1008	TC	1449 4 CR 1449 4 CS	FeP 00 FeP 01	SPCC
1.0332	DD 11 / StW 22	A 621 (1008)	1 C	1449 4 HR; 14 HR	FeP 11	SPHD
1.0333	USt 3 (DCO3G1) Ust 13	A 619 (1008)	E	1449 2 CR; 3 CR	FeP 02	SPCD
1.0334	Ust W 23(DD12G1)	A 621 (1008)	2 C	-	FeP 12	SPHE
1.0335	DD13 / StW 24	A 622 (1008)	3 C	1449 1 HR	FeP 13	SPHE
1.0338	DC04 St4 / St 14	A 620 (1008)	ES	1449 1 CR; 2 CR	FeP 04	SPCE
1.0425	P265GH H 11	-	A 42 CP / AP	1501 Gr.161-400/ 151-400 1501 Gr.164-360/ 161-400 1501 Gr.164-400/ 154-400	Fe 410-1 KW / KG / KT Fe 410 2 KW / KG	SPV 315/ SPV 355 SG 295/ SGV 410 SGV 450/ SGV 480
1.0473	P355GH 19 Mn 6	A 573 Cl. 1 A 414 Gr. G A 612	A 52 CP / AP	-	Fe E 355 - 2	SGV 410 SGV 450 SGV 480
1.0481	P295GH 17 Mn 4	A 516 Gr. 70 A 515 Gr. 70 A 414 Gr. F / G	A 48 CP / AP	1501 Gr. 224 3059-400	Fe 510-1 KG / KT / KW Fe 510-2 KG / KT / KW Fe 295	SG 365 SGV 410 SGV 450 SGV 480
1.0553	S333JO / St 52-3U	A 572 Gr. 50	E 36-3	4360-50C	Fe 510 C	-
1.0570	S355J2G3 St 52-3 N	1024 / 1524 A572 Gr. 50	E 36-3 E 36-4	Fe 510 D1 FF 1449 50/35 HR.HS 4360 - 50 D 6323-ERW 5. CEW 5. SAW 5	Fe 510 C FN Fe 510 B / C / D Fe 510 B FN	SM 490 A / B / C YA / YB
1.0577	S355J2G4 (Fe 510 D 2)	A 738	A 52 FP	Fe 510 D1 FF 1501 Gr. 224-460 1501 Gr. 224-490	-	-

A short general listing of popular steel materials

copyright 2011 maryland metrics ver gg08c

The standards that correspond with DIN Material Numbers can only be compared approximately.

The use of these equivalents has to be evaluated on a case-by-case basis.

http://gang.josen.net 常州仁成金属精密钢管厂 钢管购买热线: 13337883086 (微信同号)