



Designation: A513/A513M – 19

Standard Specification for Electric-Resistance-Welded Carbon and Alloy Steel Mechanical Tubing¹

This standard is issued under the fixed designation A513/A513M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reappraisal. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reappraisal.

1. Scope*

1.1 This specification covers electric-resistance-welded carbon and alloy steel tubing for use as mechanical tubing.

1.2 This specification covers mechanical tubing made from hot- or cold-rolled steel.

1.3 This specification covers round, square, rectangular, and special shape tubing.

Type	Size Range (Round Tubing)
Electric-Resistance-Welded Tubing from Hot-Rolled Steel	outside diameter from ½ to 15 in. [10 to 380 mm] wall from 0.065 to 0.650 in. [1.65 to 16.50 mm]
Electric-Resistance-Welded Tubing from Cold-Rolled Steel	outside diameter from ⅜ to 12 in. [9.5 to 305 mm] wall from 0.022 to 0.134 in. [0.56 to 3.40 mm]

1.4 Optional supplementary requirements are provided and when desired, shall be so stated in the order.

1.5 The values stated in either SI units or inch-pound units are to be regarded separately as standard. Within the text the SI units are shown in brackets. The values stated in each system may not be exact equivalents; therefore each system shall be used independently of the other. Combining values from the two systems may result in non-conformance with the standard. The inch-pound units shall apply unless the “M” designation of this specification is specified in the order. In this specification hard or rationalized conversions apply to diameters, lengths and tensile properties. Soft conversion applies to other SI measurements.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.09 on Carbon Steel Tubular Products.

Current edition approved March 1, 2019. Published March 2019. Originally approved in 1964. Last previous edition approved in 2018 as A513/A513M – 18. DOI: 10.1520/A0513_A0513M-19.

2. Referenced Documents

2.1 ASTM Standards:²

A370 Test Methods and Definitions for Mechanical Testing of Steel Products

A700 Guide for Packaging, Marking, and Loading Methods for Steel Products for Shipment

A751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

A1008/A1008M Specification for Steel, Sheet, Cold-Rolled, Carbon, Structural, High-Strength Low-Alloy, High-Strength Low-Alloy with Improved Formability, Solution Hardened, and Bake Hardenable

A1011/A1011M Specification for Steel, Sheet and Strip, Hot-Rolled, Carbon, Structural, High-Strength Low-Alloy, High-Strength Low-Alloy with Improved Formability, and Ultra-High Strength

A1039/A1039M Specification for Steel, Sheet, Hot Rolled, Carbon, Commercial, Structural, and High-Strength Low-Alloy, Produced by Twin-Roll Casting Process

A1040 Guide for Specifying Harmonized Standard Grade Compositions for Wrought Carbon, Low-Alloy, and Alloy Steels

E213 Practice for Ultrasonic Testing of Metal Pipe and Tubing

E273 Practice for Ultrasonic Testing of the Weld Zone of Welded Pipe and Tubing

E309 Practice for Eddy Current Examination of Steel Tubular Products Using Magnetic Saturation

E570 Practice for Flux Leakage Examination of Ferromagnetic Steel Tubular Products

2.2 ASME Standard:³

B46.1 Surface Texture

2.3 Military Standards:⁴

MIL-STD-129 Marking for Shipment and Storage

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

³ Available from American Society of Mechanical Engineers (ASME), ASME International Headquarters, Two Park Ave., New York, NY 10016-5990, http://www.asme.org.

⁴ Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111-5094, Attn: NPODS.

*A Summary of Changes section appears at the end of this standard


A513/A513M – 19

2.4 *Federal Standard*:⁴
Fed. Std. No. 123 Marking for Shipments (Civil Agencies)

3. Ordering Information

3.1 Orders for material under this specification should include the following as required to adequately describe the desired material:

- 3.1.1 Quantity (feet, metres, or number of lengths),
- 3.1.2 Name of material (electric resistance-welded carbon or alloy steel mechanical tubing),
- 3.1.3 Types, conditions and code letters, (See Sections 1 and 12),
- 3.1.4 Thermal condition, (See 12.2),
- 3.1.5 Flash condition, (See 12.3),
- 3.1.6 Grade designation, if required, (See Section 5),
- 3.1.7 Report chemical analysis and product analysis, if required (See Sections 6 and 7),
- 3.1.8 Individual supplementary requirements, if required (S1 to S10, inclusive),
- 3.1.9 Cross section (round, square, rectangular and special shapes),
- 3.1.10 Dimensions, round, outside and inside and wall thickness (See 8.1 and 8.2) or square and rectangular, outside dimension and wall thickness and corner radii, if required (See 9.1 and 9.2),
- 3.1.11 Length, round, mill lengths or definite cut length (See 8.3), square and rectangular, specified length (See 9.4),
- 3.1.12 Squareness of cut, round tubing, if required, (See 8.4),
- 3.1.13 Burrs removed, if required (See 11.2),
- 3.1.14 Protective coating (See 14.1),
- 3.1.15 Special packaging (See 17.1),
- 3.1.16 Specification designation,
- 3.1.17 End use,
- 3.1.18 Special requirements,
- 3.1.19 Special marking (See Section 16), and
- 3.1.20 Straightness Test Method (See 8.5 and 9.6).

4. Materials and Manufacture

4.1 The steel may be made by any process.

TABLE 1 Chemical Requirements for Standard Low-Carbon Steels^A

NOTE 1— Chemistry represents heat analysis. Product analysis, except for rimmed or capped steel, is to be in accordance with usual practice as shown in Table 3.

Grade Designation	Chemical Composition Limits, %			
	Carbon	Manganese	Phosphorus, max	Sulfur, max
MT ^B 1010	0.02–0.15	0.30–0.60	0.035	0.035
MT 1015	0.10–0.20	0.30–0.60	0.035	0.035
MT X 1015	0.10–0.20	0.60–0.90	0.035	0.035
MT 1020	0.15–0.25	0.30–0.60	0.035	0.035
MT X 1020	0.15–0.25	0.70–1.00	0.035	0.035

^A Rimmed or capped steels which may be used for the above grades are characterized by a lack of uniformity in their chemical composition, and for this reason product analysis is not technologically appropriate unless misapplication is clearly indicated.

^B The letters MT under grade designation indicate Mechanical Tubing.

4.2 If a specific type of melting is required by the purchaser, it shall be as stated on the purchase order.

4.3 The primary melting may incorporate separate degassing or refining, and may be followed by secondary melting, such as electroslag or vacuum-arc remelting. If secondary melting is employed, the heat shall be defined as all of the ingots remelted from a single primary heat.

4.4 Steel may be cast in ingots or may be strand cast. When steel of different grades is sequentially strand cast, identification of the resultant transition material is required. The producer shall remove the transition material by an established procedure that positively separates the grades.

4.5 Tubes shall be made by the electric-resistance-welded process and shall be made from hot- or cold-rolled steel as specified.

4.5.1 The weld shall not be located within the radius of the corners of any shaped tube unless specified by the purchaser.

5. Chemical Composition

5.1 The steel shall conform to the requirements as to chemical composition prescribed in Table 1 or Table 2 (See Specification A1040). If no grade is specified, Grades MT 1010 to MT 1020 may be furnished. Analyses of steels other than those listed are available. To determine their availability, the purchaser should contact the producer.

5.2 When a carbon steel grade is ordered under this specification, supplying an alloy grade that specifically requires the addition of any element other than those listed for the ordered grade in Tables 1 and 2 is not permitted.

5.3 Mechanical tubing with improved ductility may be produced from Drawing Steel (Types A and B), Deep Drawing Steel, or Extra Deep Drawing Steels identified in Specifications A1008/A1008M, A1011/A1011M, or A1039/A1039M. Those Specifications offer guidance in the form of nonmandatory Typical Ranges of Mechanical Properties.

6. Heat Analysis

6.1 An analysis of each heat of steel shall be made by the steel manufacturer to determine the percentages of the elements specified; if secondary melting processes are employed, the heat analysis shall be obtained from one remelted ingot or the product of one remelted ingot of each primary melt. The heat analysis shall conform to the requirements specified, except that where the heat identity has not been maintained or where the analysis is not sufficiently complete to permit conformance to be determined, the chemical composition determined from a product analysis made by the tubular manufacturer shall conform to the requirements specified for heat analysis. When requested in the order or contract, a report of such analysis shall be furnished to the purchaser.

7. Product Analysis

7.1 When requested on the purchase order, a product analysis shall be made by the supplier. The number and source of samples for such product analysis shall be based on the individual heat or lot identity of one of the following forms of material:

ASTM A513/A513M – 19

TABLE 2 Chemical Requirements for Other Carbon and Alloy Steels^A

NOTE 1—Chemistry represents heat analysis. Product analysis, except for rimmed or capped steel, is to be in accordance with usual practice as shown in Table 3.

Grade Designation	Chemical Composition Limits, %							
	Carbon	Manganese	Phosphorus, max	Sulfur, max	Silicon	Nickel	Chromium	Molybdenum
1006	0.08 max	0.45 max	0.030	0.035
1008	0.10 max	0.50 max	0.035	0.035
1009	0.15 max	0.60 max	0.035	0.035
1010	0.08–0.13	0.30–0.60	0.035	0.035
1012	0.10–0.15	0.30–0.60	0.035	0.035
1015	0.13–0.18	0.30–0.60	0.035	0.035
1016	0.13–0.18	0.60–0.90	0.035	0.035
1017	0.15–0.20	0.30–0.60	0.035	0.035
1018	0.15–0.20	0.60–0.90	0.035	0.035
1019	0.15–0.20	0.70–1.00	0.035	0.035
1020	0.18–0.23	0.30–0.60	0.035	0.035
1021	0.18–0.23	0.60–0.90	0.035	0.035
1022	0.18–0.23	0.70–1.00	0.035	0.035
1023	0.20–0.25	0.30–0.60	0.035	0.035
1024	0.18–0.25	1.30–1.65	0.035	0.035
1025	0.22–0.28	0.30–0.60	0.035	0.035
1026	0.22–0.28	0.60–0.90	0.035	0.035
1027	0.22–0.29	1.20–1.55	0.035	0.035
1030	0.28–0.34	0.60–0.90	0.035	0.035
1033	0.30–0.36	0.70–1.00	0.035	0.035
1035	0.32–0.38	0.60–0.90	0.035	0.035
1040	0.37–0.44	0.60–0.90	0.040	0.050
1050	0.48–0.55	0.60–0.90	0.040	0.050
1060	0.55–0.65	0.60–0.90	0.040	0.050
1340	0.38–0.43	1.60–1.90	0.035	0.040	0.15–0.35
1524	0.19–0.25	1.35–1.65	0.040	0.050
4118	0.18–0.23	0.70–0.90	0.035	0.040	0.15–0.35	...	0.40–0.60	0.08–0.15
4130	0.28–0.33	0.40–0.60	0.035	0.040	0.15–0.35	...	0.80–1.10	0.15–0.25
4140	0.38–0.43	0.75–1.00	0.035	0.040	0.15–0.35	...	0.80–1.10	0.15–0.25
5130	0.28–0.33	0.70–0.90	0.035	0.040	0.15–0.35	...	0.80–1.10	...
8620	0.18–0.23	0.70–0.90	0.035	0.040	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25
8630	0.28–0.33	0.70–0.90	0.035	0.040	0.15–0.35	0.40–0.70	0.40–0.60	0.15–0.25

^A Where the ellipsis (...) appears in this table, there is no requirement.

7.1.1 *Heat Identity Maintained*—One product analysis per heat shall be made on either the flat-rolled stock or tube.

7.1.2 *Heat Identity Not Maintained*—A product from one tube per 2000 ft [600 m] or less for sizes over 3 in. [75 mm], and one tube per 5000 ft [1500 m] or less for sizes 3 in. [75 mm] and under.

7.2 Samples for product analysis shall be taken in accordance with Practice A751. The composition thus determined shall correspond to the requirements of Table 1 or Table 2.

7.3 If the original test for product analysis fails, retests of two additional lengths of flat-rolled stock or tubes shall be made. Both retests for the elements in question shall meet the requirements of the specification; otherwise, all remaining material in the heat or lot shall be rejected or, at the option of the producer, each length of flat-rolled stock or tube may be individually tested for acceptance. Lengths of flat-rolled stock or tubes which do not meet the requirements of the specification shall be rejected.

8. Permissible Variations in Dimensions for Round Tubing

8.1 *Diameter and Wall Thickness (Hot-Rolled Steel)*—Variations from specified outside diameter for “as-welded” and “as-welded and annealed” tubing made from hot-rolled steel shall not exceed the amounts prescribed in Table 4. Permissible

TABLE 3 Tolerances for Product Analysis for Steels Shown in Tables 1 and 2^{A,B}

Element	Limit, or Maximum of Specified Range, %	Variation, Over the Maximum Limit or Under the Minimum Limit	
		Under min, %	Over max, %
Carbon	to 0.15, incl	0.02	0.03
	over 0.15 to 0.40, incl	0.03	0.04
	over 0.40 to 0.55, incl	0.03	0.05
Manganese	to 0.60, incl	0.03	0.03
	over 0.60 to 1.15, incl	0.04	0.04
	over 1.15 to 1.65, incl	0.05	0.05
Phosphorus	0.01
Sulfur	0.01
Silicon	to 0.30, incl	0.02	0.03
	over 0.30 to 0.60	0.05	0.05
Nickel	to 1.00, incl	0.03	0.03
Chromium	to 0.90, incl	0.03	0.03
	over 0.90 to 2.10, incl	0.05	0.05
Molybdenum	to 0.20, incl	0.01	0.01
	over 0.20 to 0.40, incl	0.02	0.02

^A Individual determinations may vary from the specified heat limits or ranges to the extent shown in this table, except that any element in a heat may not vary both above and below a specified range.

^B Where the ellipsis (...) appears in this table, there is no requirement.

variations in outside diameter for tubing that has been sink-drawn for closer tolerance on outside diameter are shown in Table 5. Permissible variations in wall thickness for tubing that

ASTM A513/A513M – 19

TABLE 4 Diameter Tolerances for Type I (A.W.H.R.) Round Tubing

NOTE 1—Measurements for diameter are to be taken at least 2 in. [50 mm] from the ends of the tubes.

Outside Diameter Range in. [mm]	Wall Thickness		Flash-in-Tubing ^{A,B}	Flash Controlled to 0.010 in. [0.26 mm] max Tubing ^{B,C}	Flash Controlled to 0.005 in. [0.13 mm]. max Tubing ^{C,D}	
	Bwg ^E	in. [mm]		Outside Diameter, ±	Outside Diameter, ±	Outside Diameter, ±
			Tolerances ^F			
				in. [mm]	in. [mm]	in. [mm]
1/2 to 1 1/8, incl [15 to 30]	16 to 10	0.065 to 0.134 [1.7 to 3.4]	0.0035 [0.09]	0.0035 [0.09]	0.0035 [0.09]	0.020 [0.51]
Over 1 1/8 to 2, incl [30 to 50]	16 to 14	0.065 to 0.083 [1.7 to 2.1]	0.005 [0.13]	0.005 [0.13]	0.005 [0.13]	0.021 [0.53]
Over 1 1/8 to 2, incl [30 to 50]	13 to 7	0.095 to 0.180 [2.4 to 4.6]	0.005 [0.13]	0.005 [0.13]	0.005 [0.13]	0.025 [0.64]
Over 1 1/8 to 2, incl [30 to 50]	6 to 5	0.203 to 0.220 [5.2 to 5.6]	0.005 [0.13]	0.005 [0.13]	0.005 [0.13]	0.029 [0.74]
Over 1 1/8 to 2, incl [30 to 50]	4 to 3	0.238 to 0.259 [6.0 to 6.6]	0.005 [0.13]	0.005 [0.13]	0.005 [0.13]	0.039 [0.99]
Over 2 to 2 1/2, incl [50 to 65]	16 to 14	0.065 to 0.083 [1.7 to 2.1]	0.006 [0.15]	0.006 [0.15]	0.006 [0.15]	0.022 [0.56]
Over 2 to 2 1/2, incl [50 to 65]	13 to 5	0.095 to 0.220 [2.4 to 5.6]	0.006 [0.15]	0.006 [0.15]	0.006 [0.15]	0.024 [0.61]
Over 2 to 2 1/2, incl [50 to 65]	4 to 3	0.238 to 0.259 [6.0 to 6.6]	0.006 [0.15]	0.006 [0.15]	0.006 [0.15]	0.040 [1.02]
Over 2 1/2 to 3, incl [65 to 75]	16 to 14	0.065 to 0.083 [1.7 to 2.1]	0.008 [0.20]	0.008 [0.20]	0.008 [0.20]	0.024 [0.61]
Over 2 1/2 to 3, incl [65 to 75]	13 to 5	0.095 to 0.220 [2.4 to 5.6]	0.008 [0.20]	0.008 [0.20]	0.008 [0.20]	0.026 [0.66]
Over 2 1/2 to 3, incl [65 to 75]	4 to 3	0.238 to 0.259 [6.0 to 6.6]	0.008 [0.20]	0.008 [0.20]	0.008 [0.20]	0.040 [1.02]
Over 2 1/2 to 3, incl [65 to 75]	2 to 0.320 [8.1]	0.284 to 0.320 [7.2 to 8.1]	0.010 [0.25]	0.010 [0.25]	0.010 [0.25]	0.048 [1.22]
Over 3 to 3 1/2, incl [75 to 90]	16 to 14	0.065 to 0.083 [1.7 to 2.1]	0.009 [0.23]	0.009 [0.23]	0.009 [0.23]	0.025 [0.64]
Over 3 to 3 1/2, incl [75 to 90]	13 to 5	0.095 to 0.220 [2.4 to 5.6]	0.009 [0.23]	0.009 [0.23]	0.009 [0.23]	0.027 [0.69]
Over 3 to 3 1/2, incl [75 to 90]	4 to 3	0.238 to 0.259 [6.0 to 6.6]	0.009 [0.23]	0.009 [0.23]	0.009 [0.23]	0.043 [1.09]
Over 3 to 3 1/2, incl [75 to 90]	2 to 0.360 [9.1]	0.284 to 0.360 [7.2 to 9.1]	0.012 [0.30]	0.012 [0.30]	0.012 [0.30]	0.050 [1.27]
Over 3 1/2 to 4, incl [90 to 100]	16 to 14	0.065 to 0.083 [1.7 to 2.1]	0.010 [0.25]	0.010 [0.25]	0.010 [0.25]	0.026 [0.66]
Over 3 1/2 to 4, incl [90 to 100]	13 to 5	0.095 to 0.220 [2.4 to 5.6]	0.010 [0.25]	0.010 [0.25]	0.010 [0.25]	0.028 [0.72]
Over 3 1/2 to 4, incl [90 to 100]	4 to 3	0.238 to 0.259 [6.0 to 6.6]	0.010 [0.25]	0.010 [0.25]	0.010 [0.25]	0.044 [1.12]
Over 3 1/2 to 4, incl [90 to 100]	2 to 0.500 [12.7]	0.284 to 0.500 [7.2 to 12.7]	0.015 [0.38]	0.015 [0.38]	0.015 [0.38]	0.053 [1.35]
Over 4 to 5, incl [100 to 130]	16 to 14	0.065 to 0.083 [1.7 to 2.1]	0.020 [0.51]	0.020 [0.51]	0.020 [0.51]	0.036 [0.91]
Over 4 to 5, incl [100 to 130]	13 to 5	0.095 to 0.220 [2.4 to 5.6]	0.020 [0.51]	0.020 [0.51]	0.020 [0.51]	0.045 [1.14]
Over 4 to 5, incl [100 to 130]	4 to 3	0.238 to 0.259 [6.0 to 6.6]	0.020 [0.51]	0.020 [0.51]	0.020 [0.51]	0.054 [1.37]
Over 4 to 5, incl [100 to 130]	2 to 0.500 [12.7]	0.284 to 0.500 [7.2 to 12.7]	0.020 [0.51]	0.020 [0.51]	0.020 [0.51]	0.058 [1.47]
Over 5 to 6, incl [130 to 150]	16 to 10	0.065 to 0.134 [1.7 to 3.4]	0.020 [0.51]	0.020 [0.51]	0.020 [0.51]	0.036 [0.91]
Over 5 to 6, incl [130 to 150]	9 to 5	0.148 to 0.220 [3.8 to 5.6]	0.020 [0.51]	0.020 [0.51]	0.020 [0.51]	0.040 [10.02]
Over 5 to 6, incl [130 to 150]	4 to 3	0.238 to 0.259 [6.0 to 6.6]	0.020 [0.51]	0.020 [0.51]	0.020 [0.51]	0.054 [1.37]
Over 5 to 6, incl [130 to 150]	2 to 0.500 [12.7]	0.284 to 0.500 [7.2 to 12.7]	0.020 [0.51]	0.020 [0.51]	0.020 [0.51]	0.058 [1.47]
Over 6 to 8, incl [150 to 200]	11 to 10	0.120 to 0.134 [3.0 to 3.4]	0.025 [0.64]	0.025 [0.64]	0.025 [0.64]	0.043 [1.09]
Over 6 to 8, incl [150 to 200]	9 to 5	0.148 to 0.220 [3.8 to 5.6]	0.025 [0.64]	0.025 [0.64]	0.025 [0.64]	0.045 [1.14]
Over 6 to 8, incl [150 to 200]	4 to 3	0.238 to 0.259 [6.0 to 6.6]	0.025 [0.64]	0.025 [0.64]	0.025 [0.64]	0.059 [1.50]
Over 6 to 8, incl [150 to 200]	2 to 0.500 [12.7]	0.284 to 0.500 [7.2 to 12.7]	0.025 [0.64]	0.025 [0.64]	0.025 [0.64]	0.063 [1.60]
Over 8 to 10, incl [200 to 250]	14 to 12	0.083 to 0.109 [2.1 to 2.8]	0.030 [0.76]	0.030 [0.76]	0.030 [0.76]	0.041 [1.04]
Over 8 to 10, incl [200 to 250]	11 to 10	0.120 to 0.134 [3.0 to 3.4]	0.030 [0.76]	0.030 [0.76]	0.030 [0.76]	0.043 [1.09]
Over 8 to 10, incl [200 to 250]	9 to 5	0.148 to 0.220 [3.8 to 5.6]	0.030 [0.76]	0.030 [0.76]	0.030 [0.76]	0.045 [1.14]
Over 8 to 10, incl [200 to 250]	4 to 3	0.238 to 0.259 [6.0 to 6.6]	0.030 [0.76]	0.030 [0.76]	0.030 [0.76]	0.059 [1.50]
Over 8 to 10, incl [200 to 250]	2 to 0.500 [12.7]	0.248 to 0.500 [7.2 to 12.7]	0.030 [0.76]	0.030 [0.76]	0.030 [0.76]	0.063 [1.60]
Over 10 to 12, incl [250 to 300]	14 to 12	0.083 to 0.109 [2.1 to 2.8]	0.035 [0.89]	0.035 [0.89]	0.035 [0.89]	0.041 [1.04]
Over 10 to 12, incl [250 to 300]	11 to 10	0.120 to 0.134 [3.0 to 3.4]	0.035 [0.89]	0.035 [0.89]	0.035 [0.89]	0.043 [1.09]
Over 10 to 12, incl [250 to 300]	9 to 5	0.148 to 0.220 [3.8 to 5.6]	0.035 [0.89]	0.035 [0.89]	0.035 [0.89]	0.045 [1.14]
Over 10 to 12, incl [250 to 300]	4 to 3	0.238 to 0.259 [6.0 to 6.6]	0.035 [0.89]	0.035 [0.89]	0.035 [0.89]	0.059 [1.50]
Over 10 to 12, incl [250 to 300]	2 to 0.500 [12.7]	0.284 to 0.500 [7.2 to 12.7]	0.035 [0.89]	0.035 [0.89]	0.035 [0.89]	0.063 [1.60]
Over 12 to 15, incl [300 to 380]	14 to 12	0.083 to 0.109 [2.1 to 2.8]	0.040 [1.02]	0.040 [1.02]	0.040 [1.02]	0.058 [1.47]
Over 12 to 15, incl [300 to 380]	11 to 10	0.120 to 0.134 [3.0 to 3.4]	0.040 [1.02]	0.040 [1.02]	0.040 [1.02]	0.058 [1.47]
Over 12 to 15, incl [300 to 380]	9 to 5	0.148 to 0.220 [3.8 to 5.6]	0.040 [1.02]	0.040 [1.02]	0.040 [1.02]	0.060 [1.52]
Over 12 to 15, incl [300 to 380]	4 to 3	0.238 to 0.259 [6.0 to 6.6]	0.040 [1.02]	0.040 [1.02]	0.040 [1.02]	0.074 [1.88]
Over 12 to 15, incl [300 to 380]	2 to 0.500 [12.7]	0.284 to 0.500 [7.2 to 12.7]	0.040 [1.02]	0.040 [1.02]	0.040 [1.02]	0.086 [2.18]

^A Flash-In-Tubing is produced only to outside diameter tolerances and wall thickness tolerances and the inside diameter welding flash does not exceed the wall thickness or 3/32 in. [2.4 mm], whichever is less.

^B Flash Controlled to 0.010 in. [0.25 mm] maximum tubing consists of tubing which is commonly produced only to outside diameter tolerances and wall thickness tolerances, in which the height of the remaining welding flash is controlled not to exceed 0.010 in.

^C Flash Controlled to 0.005 in. [0.13 mm] maximum tubing is produced to outside diameters and wall thickness tolerance, inside diameter and wall thickness tolerances, or outside diameters and inside diameter tolerances, in which the height of the remaining flash is controlled not to exceed 0.005 in. Any remaining flash is considered to be part of the applicable inside diameter tolerances.

 **A513/A513M – 19**

^D No Flash tubing is further processed by DOM for closer tolerances, produced to outside diameter and wall, inside diameter and wall, or outside diameter and inside diameter, with no dimensional indication of inside diameter flash, and is available in Types 5 and 6.

^E Birmingham Wire Gauge.

^F The ovality shall be within the above tolerances except when the wall thickness is less than 3 % of the outside diameter, in such cases see 8.6.1.

TABLE 5 Diameter Tolerances for Types 3, 4, 5, and 6 (S.D.H.R., S.D.C.R., DOM, and S.S.I.D) Round Tubing

NOTE 1—Measurements for diameter are to be taken at least 2 in. [50 mm] from the ends of the tubes.

OD Size Range ^A in. [mm]	Wall % of OD	Types 3, 4, (Sink Drawn) ^{A,B} and 5, 6, (DOM) ^{B,C} OD		Types 5 and 6 (DOM) ^{B,C} ID	
		Over in. [mm]	Under in. [mm]	Over in. [mm]	Under in. [mm]
Up to 0.499 [12.67]	all	0.004 [0.10]	0.000 [0.00]
0.500 to 1.699 [12.70 to 43.15]	all	0.005 [0.13]	0.000 [0.00]	0.000 [0.00]	0.005 [0.13]
1.700 to 2.099 [43.18 to 53.31]	all	0.006 [0.15]	0.000 [0.00]	0.000 [0.00]	0.006 [0.15]
2.100 to 2.499 [53.34 to 63.47]	all	0.007 [0.18]	0.000 [0.00]	0.000 [0.00]	0.007 [0.18]
2.500 to 2.899 [63.50 to 73.63]	all	0.008 [0.20]	0.000 [0.00]	0.000 [0.00]	0.008 [0.20]
2.900 to 3.299 [73.66 to 83.79]	all	0.009 [0.23]	0.000 [0.00]	0.000 [0.00]	0.009 [0.23]
3.300 to 3.699 [83.82 to 93.95]	all	0.010 [0.25]	0.000 [0.00]	0.000 [0.00]	0.010 [0.25]
3.700 to 4.099 [93.98 to 104.11]	all	0.011 [0.28]	0.000 [0.00]	0.000 [0.00]	0.011 [0.28]
4.100 to 4.499 [104.14 to 114.27]	all	0.012 [0.30]	0.000 [0.00]	0.000 [0.00]	0.012 [0.30]
4.500 to 4.899 [114.30 to 124.43]	all	0.013 [0.33]	0.000 [0.00]	0.000 [0.00]	0.013 [0.33]
4.900 to 5.299 [124.46 to 134.59]	all	0.014 [0.36]	0.000 [0.00]	0.000 [0.00]	0.014 [0.36]
5.300 to 5.549 [134.62 to 140.94]	all	0.015 [0.38]	0.000 [0.00]	0.000 [0.00]	0.015 [0.38]
5.550 to 5.999 [140.97 to 152.37]	under 6	0.010 [0.25]	0.010 [0.25]	0.010 [0.25]	0.010 [0.25]
	6 and over	0.009 [0.23]	0.009 [0.23]	0.009 [0.23]	0.009 [0.23]
6.000 to 6.499 [152.40 to 165.07]	under 6	0.013 [0.33]	0.013 [0.33]	0.013 [0.33]	0.013 [0.33]
	6 and over	0.010 [0.25]	0.010 [0.25]	0.010 [0.25]	0.010 [0.25]
6.500 to 6.999 [165.10 to 177.77]	under 6	0.015 [0.38]	0.015 [0.38]	0.015 [0.38]	0.015 [0.38]
	6 and over	0.012 [0.30]	0.012 [0.30]	0.012 [0.30]	0.012 [0.30]
7.000 to 7.499 [177.80 to 190.47]	under 6	0.018 [0.46]	0.018 [0.46]	0.018 [0.46]	0.018 [0.46]
	6 and over	0.013 [0.33]	0.013 [0.33]	0.013 [0.33]	0.013 [0.33]
7.500 to 7.999 [190.50 to 203.17]	under 6	0.020 [0.51]	0.020 [0.51]	0.020 [0.51]	0.020 [0.51]
	6 and over	0.015 [0.38]	0.015 [0.38]	0.015 [0.38]	0.015 [0.38]
8.000 to 8.499 [203.20 to 215.87]	under 6	0.023 [0.58]	0.023 [0.58]	0.023 [0.58]	0.023 [0.58]
	6 and over	0.016 [0.41]	0.016 [0.41]	0.016 [0.41]	0.016 [0.41]
8.500 to 8.999 [215.90 to 228.57]	under 6	0.025 [0.64]	0.025 [0.66]	0.025 [0.66]	0.025 [0.64]
	6 and over	0.017 [0.43]	0.017 [0.43]	0.017 [0.43]	0.017 [0.43]
9.000 to 9.499 [228.60 to 241.27]	under 6	0.028 [0.71]	0.028 [0.71]	0.028 [0.71]	0.028 [0.71]
	6 and over	0.019 [0.48]	0.019 [0.48]	0.019 [0.48]	0.019 [0.48]
9.500 to 9.999 [241.30 to 253.97]	under 6	0.030 [0.76]	0.030 [0.76]	0.030 [0.76]	0.030 [0.76]
	6 and over	0.020 [0.51]	0.020 [0.51]	0.020 [0.51]	0.020 [0.51]
10.000 to 10.999 [254.00 to 279.37]	all	0.034 [0.85]	0.034 [0.85]	0.034 [0.85]	0.034 [0.85]
11.000 to 11.999 [279.40 to 304.77]	all	0.035 [0.89]	0.035 [0.89]	0.035 [0.89]	0.035 [0.89]
12.000 to 12.999 [304.80 to 330.17]	all	0.036 [0.91]	0.036 [0.91]	0.036 [0.94]	0.036 [0.91]
13.000 to 13.999 [330.20 to 355.57]	all	0.037 [0.94]	0.037 [0.94]	0.037 [0.94]	0.037 [0.94]
14.000 to 14.999 [355.60 to 380.97]	all	0.038 [0.97]	0.038 [0.97]	0.038 [0.97]	0.038 [0.97]

^A Tubing, flash in or flash controlled which is further processed without mandrel to obtain tolerances closer than those shown in Tables 4 and 10.

^B The ovality shall be within the above tolerances except when the wall thickness is less than 3 % of the outside diameter, in such cases see 8.6.2.

^C Tubing produced to outside diameter and wall thickness, or inside diameter and wall thickness, or outside diameter and inside diameter, by DOM to obtain tolerances closer than those shown in Tables 4 and 10 and no dimensional indication of inside diameter flash.

has been sink-drawn for closer tolerances on outside diameters are ±10 % of the nominal wall or ±0.010 in. [0.25 mm], whichever is greater. Permissible variations in wall thickness for tubing made from hot-rolled steel are shown in Tables 6 and 7. Permissible variation in outside and inside diameter for tubing made from hot-rolled steel that has been Drawn Over a Mandrel (DOM) for closer tolerances are shown in Table 5 with wall tolerances shown in Tables 8 and 9.

8.2 Diameter and Wall Thickness (Cold-Rolled Steel)—Variations in outside diameter and inside diameter of “as-welded” and “as-welded and annealed” tubing made from cold-rolled steel are shown in Table 10. Outside diameter tolerances for cold-rolled steel tubing, sink drawn and DOM, are shown in Table 5. Wall thickness tolerances for “as-welded” tubing made from cold-rolled steel are shown in

Tables 11 and 12. Permissible variations in wall thickness for round tubing, DOM for closer tolerances, are shown in Tables 8 and 9. Permissible variations in wall thickness for tubing that has been sink-drawn for closer tolerances on outside diameter are ±10 % of the nominal wall or ±0.010 in. [0.25 mm], whichever is greater.

8.3 Length (Hot- and Cold-Rolled Steel)—Mechanical tubing is commonly furnished in mill lengths 5 ft [1.5 m] and over. Definite cut lengths are furnished when specified by the purchaser. Tolerances for definite cut lengths round tubing shall be as given in Tables 13 and 14.

8.4 Squareness of Cut (Hot- and Cold-Rolled Steel)—When specified, tolerance for squareness of cut of round tubing shall be as given in Table 15. Measurements are made with use of an

 **A513/A513M - 19**

TABLE 6 Wall Thickness Tolerance for Type I (A.W.H.R.) Round Tubing (Inch Units)

Wall Thickness		Outside Diameter, ^A																			
in. ^A	Bwg ^A	¾ to 1, incl		Over 1 to 1 15/16, incl		Over 1 15/16 to 3 3/4, incl		Over 3 3/4 to 4 1/2, incl		Over 4 1/2 to 6, incl		Over 6 to 8, incl		Over 8 to 10, incl		Over 10 to 12, incl		Over 12 to 15, incl			
		+	-	+	-	+	-	+	-	+	-	+	-	+	-	+	-	+	-		
Wall Thickness Tolerances, in., ± ^B																					
0.065	16	0.005	0.009	0.004	0.010	0.003	0.011	0.002	0.012	0.002	0.012	0.002	0.012	0.002	0.012	0.003	0.013	0.003	0.013	0.003	0.013
0.072	15	0.005	0.009	0.004	0.010	0.003	0.011	0.002	0.012	0.002	0.012	0.002	0.012	0.002	0.012	0.003	0.013	0.003	0.013	0.003	0.013
0.083	14	0.006	0.010	0.005	0.011	0.004	0.012	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013
0.095	13	0.006	0.010	0.005	0.011	0.004	0.012	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013
0.109	12	0.006	0.010	0.005	0.011	0.004	0.012	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013
0.120	11	0.006	0.010	0.005	0.011	0.004	0.012	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013
0.134	10	0.006	0.010	0.005	0.011	0.004	0.012	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013	0.003	0.013
0.148	9	0.006	0.012	0.005	0.013	0.004	0.014	0.004	0.014	0.004	0.014	0.004	0.014	0.004	0.014	0.004	0.014	0.004	0.014
0.165	8	0.006	0.012	0.005	0.013	0.004	0.014	0.004	0.014	0.004	0.014	0.004	0.014	0.004	0.014	0.004	0.014	0.004	0.014
0.180	7	0.006	0.012	0.005	0.013	0.004	0.014	0.004	0.014	0.004	0.014	0.004	0.014	0.004	0.014	0.004	0.014	0.004	0.014
0.203	6	0.006	0.012	0.007	0.015	0.006	0.016	0.005	0.017	0.005	0.017	0.005	0.017	0.005	0.017	0.005	0.017	0.005	0.017
0.220	5	0.007	0.015	0.006	0.016	0.005	0.017	0.005	0.017	0.005	0.017	0.005	0.017	0.005	0.017	0.005	0.017
0.238	4	0.012	0.020	0.011	0.021	0.010	0.022	0.010	0.022	0.010	0.022	0.010	0.022	0.010	0.022	0.010	0.022
0.259	3	0.013	0.021	0.012	0.022	0.011	0.023	0.011	0.023	0.011	0.023	0.011	0.023	0.011	0.023	0.011	0.023
0.284	2	0.014	0.022	0.013	0.023	0.012	0.024	0.012	0.024	0.012	0.024	0.012	0.024	0.012	0.024	0.012	0.024
0.300	1	0.015	0.023	0.014	0.024	0.013	0.025	0.013	0.025	0.013	0.025	0.013	0.025	0.013	0.025	0.013	0.025
0.320		0.016	0.024	0.015	0.025	0.014	0.026	0.014	0.026	0.014	0.026	0.014	0.026	0.014	0.026	0.014	0.026
0.344		0.017	0.025	0.016	0.026	0.015	0.027	0.015	0.027	0.015	0.027	0.015	0.027	0.015	0.027	0.015	0.027
0.360		0.017	0.025	0.016	0.026	0.015	0.027	0.015	0.027	0.015	0.027	0.015	0.027	0.015	0.027	0.015	0.027
0.375		0.017	0.026	0.016	0.027	0.015	0.027	0.015	0.027	0.015	0.027	0.015	0.027	0.015	0.027
0.406		0.017	0.027	0.016	0.028	0.016	0.028	0.016	0.028	0.016	0.028	0.016	0.028	0.016	0.028
0.438		0.017	0.027	0.016	0.028	0.016	0.028	0.016	0.028	0.016	0.028	0.016	0.028	0.016	0.028
0.469		0.027	0.016	0.028	0.016	0.028	0.016	0.028	0.016	0.028	0.016	0.028	0.016	0.028
0.500		0.016	0.028	0.016	0.028	0.016	0.028	0.016	0.028	0.016	0.028	0.016	0.028

^A Birmingham Wire Gauge.

^B Where the ellipsis (...) appears in this table, the tolerance is not addressed.

 **A513/A513M - 19**

TABLE 7 Wall Thickness Tolerance for Type I (A.W.H.R.) Round Tubing (SI Units)

Wall Thickness mm	Outside Diameter, mm																	
	20 to 25 mm, incl		Over 25 to 50 mm, incl		Over 50 to 95 mm, incl		Over 95 to 115 mm incl		Over 115 to 150 mm incl		Over 150 to 200 mm Incl		Over 200 to 250 mm incl		Over 250 to 305 mm Incl		Over 305 to 380 mm, incl	
	+	-	+	-	+	-	+	-	+	-	+	-	+	-	+	-	+	-
1.65	0.13	0.23	0.10	0.25	0.08	0.28	0.30	0.05	0.30	0.05	0.30	0.05	0.30	0.30	0.30	0.05	0.30	0.30
1.83	0.13	0.23	0.10	0.25	0.08	0.28	0.30	0.05	0.30	0.05	0.30	0.05	0.30	0.30	0.30	0.05	0.30	0.30
2.11	0.15	0.25	0.13	0.28	0.10	0.30	0.33	0.08	0.33	0.08	0.33	0.08	0.33	0.33	0.33	0.08	0.33	0.33
2.41	0.15	0.25	0.13	0.28	0.10	0.30	0.33	0.08	0.33	0.08	0.33	0.08	0.33	0.33	0.33	0.08	0.33	0.33
2.77	0.15	0.25	0.13	0.28	0.10	0.30	0.33	0.08	0.33	0.08	0.33	0.08	0.33	0.33	0.33	0.08	0.33	0.33
3.05	0.15	0.25	0.13	0.28	0.10	0.30	0.33	0.08	0.33	0.08	0.33	0.08	0.33	0.33	0.33	0.08	0.33	0.33
3.40	0.15	0.25	0.13	0.28	0.10	0.30	0.33	0.08	0.33	0.08	0.33	0.08	0.33	0.33	0.33	0.08	0.33	0.33
3.76	0.15	0.30	0.13	0.33	0.36	0.10	0.36	0.10	0.36	0.10	0.36	0.36	0.36	0.10	0.36	0.36
4.19	0.15	0.30	0.13	0.33	0.36	0.10	0.36	0.10	0.36	0.10	0.36	0.36	0.36	0.10	0.36	0.36
4.57	0.16	0.30	0.13	0.33	0.36	0.10	0.36	0.10	0.36	0.10	0.36	0.36	0.36	0.10	0.36	0.36
5.16	0.18	0.38	0.41	0.13	0.43	0.13	0.43	0.13	0.43	0.43	0.43	0.13	0.43	0.43
5.59	0.18	0.38	0.41	0.13	0.43	0.13	0.43	0.13	0.43	0.43	0.43	0.13	0.43	0.43
6.05	0.30	0.51	0.53	0.25	0.56	0.25	0.56	0.25	0.56	0.56	0.56	0.25	0.56	0.56
6.58	0.33	0.53	0.56	0.28	0.58	0.28	0.58	0.28	0.58	0.58	0.58	0.28	0.58	0.58
7.21	0.36	0.56	0.58	0.30	0.61	0.30	0.61	0.30	0.61	0.61	0.61	0.30	0.61	0.61
7.62	0.38	0.58	0.61	0.33	0.64	0.33	0.64	0.33	0.64	0.64	0.64	0.33	0.64	0.64
8.13	0.41	0.61	0.64	0.36	0.66	0.36	0.66	0.36	0.66	0.66	0.66	0.36	0.66	0.66
8.74	0.43	0.64	0.66	0.38	0.69	0.38	0.69	0.38	0.69	0.69	0.69	0.38	0.69	0.69
9.14	0.43	0.64	0.66	0.38	0.69	0.38	0.69	0.38	0.69	0.69	0.69	0.38	0.69	0.69
9.53	0.41	0.41	0.71	0.41	0.71	0.41	0.71	0.71	0.71	0.41	0.71	0.71
10.31	0.43	0.43	0.71	0.41	0.71	0.41	0.71	0.71	0.71	0.41	0.71	0.71
11.13	0.43	0.43	0.71	0.41	0.71	0.41	0.71	0.71	0.71	0.41	0.71	0.71
11.91	0.71	0.41	0.71	0.41	0.71	0.71	0.71	0.41	0.71	0.71
12.70	0.41	0.71	0.41	0.71	0.41	0.71	0.71	0.71	0.41	0.71	0.71

^A Where the ellipsis (...) appears in this table, the tolerance is not addressed.

ASTM A513/A513M – 19

TABLE 8 Wall Thickness Tolerances of Types 5 and 6 (DOM and S.S.I.D.) Round Tubing (Inch Units)

		Outside Diameter, in. ^A							
Wall Thickness		% to 7/8, incl		Over 7/8 to 1 1/8, incl		Over 1 1/8 to 3 3/4, incl		Over 3 3/4 to 15, incl	
in. ^A	Bwg ^A	Wall Thickness Tolerances, in., ^{A,B} ±							
		+	-	+	-	+	-	+	-
0.035	20	0.002	0.002	0.002	0.002	0.002	0.002
0.049	18	0.002	0.002	0.002	0.003	0.002	0.003
0.065	16	0.002	0.002	0.002	0.003	0.002	0.003	0.004	0.004
0.083	14	0.002	0.002	0.002	0.003	0.003	0.003	0.004	0.005
0.095	13	0.002	0.002	0.002	0.003	0.003	0.003	0.004	0.005
0.109	12	0.002	0.003	0.002	0.004	0.003	0.003	0.005	0.005
0.120	11	0.003	0.003	0.002	0.004	0.003	0.003	0.005	0.005
0.134	10	0.002	0.004	0.003	0.003	0.005	0.005
0.148	9	0.002	0.004	0.003	0.003	0.005	0.005
0.165	8	0.003	0.004	0.003	0.004	0.005	0.006
0.180	7	0.004	0.004	0.003	0.005	0.006	0.006
0.203	6	0.004	0.005	0.004	0.005	0.006	0.007
0.220	5	0.004	0.006	0.004	0.006	0.007	0.007
0.238	4	0.005	0.006	0.005	0.006	0.007	0.007
0.259	3	0.005	0.006	0.005	0.006	0.007	0.007
0.284	2	0.005	0.006	0.005	0.006	0.007	0.007
0.300	1	0.006	0.006	0.006	0.006	0.008	0.008
0.320	0.007	0.007	0.007	0.007	0.008	0.008
0.344	0.008	0.008	0.008	0.008	0.009	0.009
0.375	0.009	0.009	0.009	0.009
0.400	0.010	0.010	0.010	0.010
0.438	0.011	0.011	0.011	0.011
0.460	0.012	0.012	0.012	0.012
0.480	0.012	0.012	0.012	0.012
0.531	0.013	0.013	0.013	0.013
0.563	0.013	0.013	0.013	0.013
0.580	0.014	0.014	0.014	0.014
0.600	0.015	0.015	0.015	0.015
0.625	0.016	0.016	0.016	0.016
0.650	0.017	0.017	0.017	0.017

^A Birmingham Wire Gauge.

^B Where the ellipsis (...) appears in this table, the tolerance is not addressed.

TABLE 9 Wall Thickness Tolerances of Types 5 and 6 (DOM and S.S.I.D.) Round Tubing (SI Units)

		Outside Diameter, mm							
Wall Thickness		10 to 20, incl		Over 20 to 50, incl		Over 50 to 100, incl		Over 100 to 380, incl	
mm		Wall Thickness Tolerances, mm ^A							
		+	-	+	-	+	-	+	-
0.89	0.05	0.05	0.05	0.05	0.05	0.05	0.05
1.24	0.05	0.05	0.05	0.08	0.05	0.08	0.05
1.65	0.05	0.05	0.05	0.08	0.05	0.08	0.08	0.10	0.10
2.11	0.05	0.05	0.05	0.08	0.08	0.08	0.08	0.10	0.13
2.41	0.05	0.05	0.05	0.08	0.08	0.08	0.08	0.10	0.13
2.77	0.05	0.08	0.05	0.10	0.08	0.08	0.08	0.13	0.13
3.05	0.08	0.08	0.05	0.10	0.08	0.08	0.08	0.13	0.13
3.40	0.05	0.10	0.08	0.08	0.08	0.13	0.13
3.76	0.05	0.10	0.08	0.08	0.08	0.13	0.13
4.19	0.08	0.10	0.08	0.10	0.13	0.15	0.15
4.57	0.10	0.10	0.08	0.13	0.15	0.15	0.15
5.16	0.10	0.13	0.10	0.13	0.15	0.18	0.18
5.59	0.10	0.15	0.10	0.15	0.18	0.18	0.18
6.05	0.13	0.15	0.13	0.15	0.18	0.18	0.18
6.58	0.13	0.15	0.13	0.13	0.18	0.18	0.18
7.21	0.13	0.15	0.13	0.15	0.18	0.18	0.18
7.62	0.15	0.15	0.15	0.15	0.20	0.20	0.20
8.13	0.18	0.18	0.18	0.18	0.20	0.20	0.20
8.74	0.20	0.20	0.20	0.20	0.23	0.23	0.23
9.53	0.23	0.23	0.23	0.23	0.23
10.16	0.25	0.25	0.25	0.25	0.25
11.13	0.28	0.28	0.28	0.28	0.28
11.68	0.30	0.30	0.30	0.30	0.30
12.19	0.30	0.30	0.30	0.30	0.30
13.49	0.33	0.33	0.33	0.33	0.33
14.3	0.33	0.33	0.33	0.33	0.33
14.73	0.36	0.36	0.36	0.36	0.36
15.24	0.38	0.38	0.38	0.38	0.38
15.88	0.41	0.41	0.41	0.016	0.016
16.51	0.43	0.43	0.43	0.43	0.43

^A Where the ellipsis (...) appears in this table, the tolerance is not addressed.

“L” square and feeler gauge. The long leg (blade) of the square to be equal to tube diameter plus a minimum of 1 in. [25.4 mm]. Outside diameter burr to be removed for measurement.

8.5 Straightness—The straightness tolerance for round tubing is 0.030 in./3 ft [0.75 mm/1 m] lengths to 8.000 in. [200 mm] outside diameter. For 8.000 in. [200 mm] outside diameter and above, straightness tolerance is 0.060 in./3 ft [1.5 mm/1 m] lengths. For lengths under 1 ft [305 mm] the straightness tolerance shall be agreed upon between the purchaser and producer. The test method for straightness measurement is at the manufacturer’s option, unless a specific test method is specified in the purchase order.

8.6 Ovality (Hot- and Cold-Rolled Steel)—Ovality is the difference between maximum and minimum outside diameters measured at any one cross section. The ovality shall be within the tolerances except when the wall thickness is less than 3 % of the outside diameter.

8.6.1 In such cases for Types 1 and 2 (A.W.H.R. and A.W.C.R.) the ovality may be 50 % greater than the outside tolerances but the mean outside diameter shall be within the specified tolerance.

8.6.2 For Types 3, 4, 5, and 6 (S.D.H.R., S.D.C.R., DOM, and S.S.I.D.) the additional ovality shall be as follows but the mean outside diameter shall be within the specified tolerance:

Outside Diameter, in. [mm]	Additional Ovality Tolerance, in. [mm]
Up to 2 [50], incl	0.010 [0.25]
Over 2 to 3 [50 to 75], incl	0.015 [0.38]
Over 3 to 4 [75 to 100], incl	0.020 [0.51]
Over 4 to 5 [100 to 125], incl	0.025 [0.64]
Over 5 to 6 [125 to 150], incl	0.030 [0.76]
Over 6 to 7 [150 to 180], incl	0.035 [0.89]
Over 7 to 8 [180 to 205], incl	0.040 [1.02]
Over 8 to 9 [205 to 230], incl	0.045 [1.14]
Over 9 to 10 [230 to 255], incl	0.050 [1.27]
Over 10 to 11 [255 to 280], incl	0.055 [1.40]
Over 11 to 12 [280 to 305], incl	0.060 [1.52]
Over 12 to 12.500 [305 to 320], incl	0.065 [1.65]

9. Permissible Variations in Dimensions of Square and Rectangular Tubing

9.1 Diameter and Wall Thickness—Permissible variations in outside dimensions for square and rectangular tubing shall be as given in **Table 16**. The wall thickness tolerance is ± 10 % of the nominal wall thickness.

9.2 Corner Radii—Unless otherwise specified, the corners of square and rectangular tubing shall be slightly rounded inside and outside, consistent with wall thickness. The outside corners may be slightly flattened. The radii of corners shall be as given in **Table 17**.

9.3 Squareness—Permissible variations for squareness shall be determined by the following equation:

ASTM A513/A513M – 19

TABLE 10 Diameter Tolerances for Type 2 (A.W.C.R.) Round Tubing

NOTE 1—Measurements for diameter are to be taken at least 2 in. [50 mm] from the ends of the tubes.

Outside Diameter Range in. [mm]	Wall Thickness		Flash-in-Tubing ^A	Flash Controlled to 0.010 in. [0.26 mm] max Tubing ^B	Flash Controlled ^C to 0.005 in. [0.13 mm] max Tubing	
	Bwg ^A	in. ^D [mm]		Outside Diameter, ±	Outside Diameter, ±	Outside Diameter, ±
			Tolerances ^{E,F}			
				in. [mm]	in. [mm]	in. [mm]
5/8 to 3/4, incl [10 to 15]	24 to 16	0.022 to 0.065 [0.56 to 1.65]	0.003 [0.08]
Over 5/8 to 1 1/8, incl [15 to 30]	24 to 19	0.022 to 0.042 [0.56 to 1.07]	0.0035 [0.09]	0.0035 [0.09]	0.0035 [0.09]	0.013 [0.33]
Over 5/8 to 1 1/8, incl [15 to 30]	18	0.049 [1.24]	0.0035 [0.09]	0.0035 [0.09]	0.0035 [0.09]	0.015 [0.38]
Over 5/8 to 1 1/8, incl [15 to 30]	16 to 14	0.065 to 0.083 [1.65 to 2.11]	0.0035 [0.09]	0.0035 [0.09]	0.0035 [0.09]	0.019 [0.48]
Over 3/4 to 1 1/8, incl [20 to 50]	13	0.095 [2.41]	0.0035 [0.09]	0.0035 [0.09]	0.0035 [0.09]	0.019 [0.48]
Over 3/4 to 1 1/8, incl [20 to 30]	12 to 11	0.109 to 0.120 [2.77 to 3.05]	0.0035 [0.09]	0.0035 [0.09]	0.0035 [0.09]	0.021 [0.53]
Over 1 1/8 to 2, incl [30 to 50]	22 to 18	0.028 to 0.049 [0.71 to 1.24]	0.005 [0.13]	0.005 [0.13]	0.005 [0.13]	0.015 [0.38]
Over 1 1/8 to 2, incl [30 to 50]	16 to 13	0.065 to 0.095 [1.65 to 2.41]	0.005 [0.13]	0.005 [0.13]	0.005 [0.13]	0.019 [0.48]
Over 1 1/8 to 2, incl [30 to 50]	12 to 10	0.109 to 0.134 [2.77 to 3.40]	0.005 [0.13]	0.005 [0.13]	0.005 [0.13]	0.022 [0.56]
Over 2 to 2 1/2, incl [50 to 65]	20 to 18	0.035 to 0.049 [0.89 to 1.24]	0.006 [0.15]	0.006 [0.15]	0.006 [0.15]	0.016 [0.41]
Over 2 to 2 1/2, incl [50 to 65]	16 to 13	0.065 to 0.095 [1.65 to 2.41]	0.006 [0.15]	0.006 [0.15]	0.006 [0.15]	0.020 [0.51]
Over 2 to 2 1/2, incl [50 to 65]	12 to 10	0.109 to 0.134 [2.77 to 3.40]	0.006 [0.15]	0.006 [0.15]	0.006 [0.15]	0.023 [0.58]
Over 2 1/2 to 3, incl [65 to 75]	20 to 18	0.035 to 0.049 [0.89 to 1.24]	0.008 [0.20]	0.008 [0.20]	0.008 [0.20]	0.018 [0.46]
Over 2 1/2 to 3, incl [65 to 75]	16 to 13	0.065 to 0.095 [1.65 to 2.41]	0.008 [0.20]	0.008 [0.20]	0.008 [0.20]	0.022 [0.56]
Over 2 1/2 to 3, incl [65 to 75]	12 to 10	0.109 to 0.134 [2.77 to 3.40]	0.008 [0.20]	0.008 [0.20]	0.008 [0.20]	0.025 [0.64]
Over 3 to 3 1/2, incl [75 to 90]	20 to 18	0.035 to 0.049 [0.89 to 1.24]	0.009 [0.23]	0.009 [0.23]	0.009 [0.23]	0.019 [0.48]
Over 3 to 3 1/2, incl [75 to 90]	16 to 13	0.065 to 0.095 [1.65 to 2.41]	0.009 [0.23]	0.009 [0.23]	0.009 [0.23]	0.023 [0.58]
Over 3 to 3 1/2, incl [75 to 90]	12 to 10	0.109 to 0.134 [2.77 to 3.40]	0.009 [0.23]	0.009 [0.23]	0.009 [0.23]	0.026 [0.66]
Over 3 1/2 to 4, incl [90 to 100]	20 to 18	0.035 to 0.049 [0.89 to 1.24]	0.010 [0.25]	0.010 [0.25]	0.010 [0.25]	0.020 [0.51]
Over 3 1/2 to 4, incl [90 to 100]	16 to 13	0.065 to 0.095 [1.65 to 2.41]	0.010 [0.25]	0.010 [0.25]	0.010 [0.25]	0.024 [0.61]
Over 3 1/2 to 4, incl [90 to 100]	12 to 10	0.109 to 0.134 [2.77 to 3.40]	0.010 [0.25]	0.010 [0.25]	0.010 [0.25]	0.027 [0.69]
Over 4 to 6, incl [100 to 150]	16 to 13	0.065 to 0.095 [1.65 to 2.41]	0.020 [0.51]	0.020 [0.51]	0.020 [0.51]	0.034 [0.85]
Over 4 to 6, incl [100 to 150]	12 to 10	0.109 to 0.134 [2.77 to 3.40]	0.020 [0.51]	0.020 [0.51]	0.020 [0.51]	0.037 [0.94]
Over 6 to 8, incl [150 to 200]	14 to 13	0.083 to 0.095 [2.11 to 2.41]	0.025 [0.64]	0.025 [0.64]	0.025 [0.64]	0.039 [0.99]
Over 6 to 8, incl [150 to 200]	12 to 10	0.109 to 0.134 [2.77 to 3.40]	0.025 [0.64]	0.025 [0.64]	0.025 [0.64]	0.042 [1.07]
Over 8 to 10, incl [200 to 250]	16 to 13	0.065 to 0.095 [1.65 to 2.41]	0.030 [0.76]	0.030 [0.76]	0.030 [0.76]	0.044 [1.12]
Over 8 to 10, incl [200 to 250]	12 to 10	0.109 to 0.134 [2.77 to 3.40]	0.030 [0.76]	0.030 [0.76]	0.030 [0.76]	0.049 [1.24]
Over 10 to 12, incl [250 to 300]	14 to 13	0.083 to 0.095 [2.11 to 2.41]	0.035 [0.89]	0.035 [0.89]	0.035 [0.89]	0.049 [1.24]
Over 10 to 12, incl [250 to 300]	12 to 10	0.109 to 0.134 [2.77 to 3.40]	0.035 [0.89]	0.035 [0.89]	0.035 [0.89]	0.054 [1.37]

^AFlash-In-Tubing is produced to outside diameter tolerances and wall thickness tolerances only, and the height of the inside welding flash does not exceed the wall thickness or 3/32 in. [2.38 mm], whichever is less.

^BFlash Controlled to 0.010 in. [0.26 mm] maximum tubing consists of tubing over 5/8 in. [15 mm] outside diameter which is commonly produced to outside diameter tolerances and wall thickness tolerances only, in which the height of the remaining inside welding flash is controlled not to exceed 0.010 in.

^CFlash Controlled to 0.005 in. [0.13 mm] maximum tubing is produced to outside diameter tolerances and wall thickness tolerances, inside diameter tolerances and wall thickness tolerances, or outside diameter tolerances and inside diameter tolerances, in which the height of the remaining inside welding flash is controlled not to exceed 0.005 in. Any remaining flash is considered to be part of the applicable inside diameter tolerances.

^DBirmingham Wire Gauge.

^EThe ovality shall be within the above tolerances except when the wall thickness is less than 3 % of the outside diameter, in such cases see 8.6.1.

^FWhere the ellipsis (...) appears in this table, the tolerance is not addressed.

$$\pm b = c \times 0.006 \text{ in. (0.15 mm)}$$

where:

b = tolerance for out-of-square, and

c = largest external dimension across flats.

The squareness of sides is commonly determined by one of the following methods.

9.3.1 A square with two adjustable contact points on each arm, is placed on two sides. A fixed feeler gauge is then used

to measure the maximum distance between the free contact point and the surface of the tubing.

9.3.2 A square equipped with a direct reading vernier, may be used to determine the angular deviation which, in turn, may be related to distance in in. [mm].

9.4 Length—Variations from the specified length shall not exceed the amount prescribed in Table 18.



TABLE 11 Wall Thickness Tolerances for Type 2 (A.W.C.R.) Round Tubing (Inch Units)

Wall Thickness in. ^A	Outside Diameter, in. ^A												
	3/8 to 7/8, incl	Over 7/8 to 1 1/8, incl	Over 1 1/8 to 3 3/4, incl	Over 3 3/4 to 5, incl	Over 5 to 6, incl	Over 6 to 8, incl	Over 8 to 10, incl	Over 10 to 12, incl	Over 12 to 14, incl	Over 14 to 16, incl	Over 16 to 18, incl	Over 18 to 20, incl	
Bwg ^B	+	-	+	-	+	-	+	-	+	-	+	-	+
0.022	0.001	0.005	0.001	0.005	0.004	0.007	0.004	0.007	0.004	0.008	0.004	0.008	0.004
0.028	0.001	0.005	0.001	0.005	0.004	0.007	0.004	0.007	0.004	0.008	0.004	0.008	0.004
0.035	0.002	0.005	0.001	0.005	0.004	0.007	0.004	0.007	0.004	0.008	0.004	0.008	0.004
0.042	0.002	0.006	0.001	0.006	0.004	0.007	0.004	0.007	0.004	0.008	0.004	0.008	0.004
0.049	0.003	0.006	0.002	0.006	0.004	0.007	0.004	0.007	0.004	0.008	0.004	0.008	0.004
0.065	0.005	0.007	0.004	0.007	0.004	0.007	0.004	0.007	0.004	0.008	0.004	0.008	0.004
0.083	0.006	0.007	0.005	0.007	0.004	0.007	0.004	0.007	0.004	0.008	0.004	0.008	0.004
0.095	0.006	0.007	0.005	0.007	0.004	0.007	0.004	0.007	0.004	0.008	0.004	0.008	0.004
0.109	0.006	0.008	0.005	0.008	0.005	0.008	0.005	0.009	0.005	0.009	0.005
0.120	0.007	0.008	0.006	0.008	0.005	0.008	0.005	0.009	0.005	0.009	0.005
0.134	0.007	0.008	0.006	0.008	0.005	0.008	0.005	0.009	0.005	0.009	0.005

^A Birmingham Wire Gauge.
^B Where the ellipsis appears in this table, the tolerance is not addressed.

TABLE 12 Wall Thickness Tolerances for Type 2 (A.W.C.R.) Round Tubing (SI Units)

Wall Thickness mm	Outside Diameter, mm															
	[10 to 20], incl		Over [20 to 50], incl		Over [50 to 100], incl		Over [100 to 130], incl		Over [130 to 150], incl		Over [150 to 205], incl		Over [205 to 250], incl		Over [250 to 305], incl	
	+	-	+	-	+	-	+	-	+	-	+	-	+	-	+	-
	Wall Thickness Tolerances, mm ^A ±															
0.56	0.03	0.13	0.03	0.13
0.71	0.03	0.13	0.03	0.13
0.89	0.05	0.13	0.03	0.13	0.03	0.13
1.07	0.05	0.15	0.03	0.15	0.03	0.15
1.24	0.08	0.15	0.05	0.15	0.05	0.15
1.65	0.13	0.18	0.10	0.18	0.10	0.18	0.10	0.18	0.10	0.18	0.10	0.18	0.10	0.18	0.10	0.18
2.11	0.15	0.18	0.13	0.18	0.10	0.18	0.10	0.18	0.10	0.18	0.10	0.18	0.10	0.18	0.10	0.18
2.41	0.15	0.18	0.13	0.18	0.10	0.18	0.10	0.18	0.10	0.18	0.10	0.18	0.10	0.18	0.10	0.18
2.77	0.15	0.20	0.13	0.20	0.13	0.20	0.13	0.20	0.13	0.20	0.13	0.20	0.13	0.20
3.05	0.18	0.20	0.15	0.20	0.15	0.20	0.15	0.20	0.15	0.20	0.15	0.20	0.15	0.20
3.40	0.18	0.20	0.15	0.20	0.15	0.20	0.15	0.20	0.15	0.20	0.15	0.20	0.15	0.20

^A Where the ellipsis appears in this table, the tolerance is not addressed.

 **A513/A513M – 19**

TABLE 13 Cut-Length Tolerances for Lathe-Cut Round Tubing

Outside Diameter in. [mm]	6 in. [150 mm] and under 12 in. [305 mm] in. [mm]	12 in. [305 mm] and under 48 in. [1200 mm] in. [mm]	48 in. [1200 mm] and under 10 ft [3000 mm] in. [mm]	10 ft [3000 mm] to 24 ft [7300 mm] incl ^A in. [mm]
3/8 to 3 incl [10 to 75]	±1/64 in. [0.40]	±1/32 in. [0.79]	±3/64 in. [1.19]	±1/8 in. [3.17]
Over 3 to 6, incl [75 to 150]	±1/32 in. [0.79]	±3/64 in. [1.19]	±1/16 in. [1.59]	±1/8 in. [3.17]
Over 6 to 9, incl [150 to 230]	±1/16 in. [1.59]	±1/16 in. [1.59]	±1/8 in. [3.17]	±1/8 in. [3.17]
Over 9 to 12, incl [230 to 305]	±3/32 in. [2.38]	±3/32 in. [2.38]	±1/8 in. [3.17]	±1/8 in. [3.17]
Over 12 to 15, incl [305 to 380]	±3/32 in. [2.38]	±3/32 in. [2.38]	±1/8 in. [3.17]	±1/8 in. [3.17]

^A For each additional 10 ft [3.0 m] or fraction thereof over 24 ft [7.3 m] an additional allowance should be made of plus or minus 1/16 in. [1.60 mm].

TABLE 14 Length Tolerances for Punch-, Saw-, or Disc-Cut Round Tubing

Outside Diameter in. [mm]	6 in. [150 mm] and under 12 in. [300 mm] in. [mm]	12 in. [300 mm] and under 48 in. [1200 mm] in. [mm]	48 in. [1200 mm] and under 10 ft [3.0 m] in. [mm]	10 ft [3.0 m] to 24 ft [73 m] incl ^A in. [mm]
3/8 to 3, incl [10 to 75]	±1/16 in. [1.59]	±1/16 in. [1.59]	±1/8 in. [3.17]	±1/4 in. [6.35]
Over 3 to 6, incl [75 to 150]	±1/16 in. [1.59]	±1/16 in. [1.59]	±1/8 in. [3.17]	±1/4 in. [6.35]
Over 6 to 9, incl [150 to 230]	±1/16 in. [1.59]	±1/16 in. [1.59]	±1/8 in. [3.17]	±1/4 in. [6.35]
Over 9 to 12, incl [230 to 305]	±1/16 in. [1.59]	±1/16 in. [1.59]	±1/8 in. [3.17]	±1/4 in. [6.35]
Over 12 to 15, incl [305 to 380]	±1/16 in. [1.59]	±1/16 in. [1.59]	±1/8 in. [3.17]	±1/4 in. [6.35]

^A For each additional 10 ft [3.0 m] or fraction thereof over 24 ft [7.3 m] an additional allowance should be made of plus or minus 1/16 in. [1.60 mm].

TABLE 15 Tolerance (Inch) for Squareness of Cut (Either End) When Specified for Round Tubing^{A,B}

Length of Tube ft [m]	Outside Diameter, in. [mm]						
	Under 1 [25] in. [mm]	1 to 2, [25 to 50] incl in. [mm]	Over 2 to 3, [25 to 75] incl in. [mm]	Over 3 to 4, [75 to 100] incl in. [mm]	Over 4 to 6, [100 to 150] incl in. [mm]	Over 6 to 10, [150 to 250] incl in. [mm]	Over 10 to 15, [250 to 380] incl in. [mm]
Under 1 [0.3]	0.006 [0.15]	0.008 [0.20]	0.010 [0.25]	0.015 [0.38]	0.020 [0.50]	0.060 [1.52]	0.080 [2.03]
1 to 3, incl [0.3 to 1]	0.008 [0.20]	0.010 [0.25]	0.015 [0.38]	0.020 [0.50]	0.030 [0.76]	0.060 [1.52]	0.080 [2.03]
Over 3 to 6, incl [1 to 2]	0.010 [0.25]	0.015 [0.38]	0.020 [0.50]	0.025 [0.63]	0.040 [1.01]	0.070 [1.77]	0.090 [2.28]
Over 6 to 9, incl [2 to 3]	0.015 [0.38]	0.020 [0.50]	0.025 [0.63]	0.030 [0.76]	0.040 [1.01]	0.070 [1.77]	0.090 [2.28]

^A Actual squareness normal to length of tube, not parallelness of both ends.

^B Values given are “go” value of feeler gauge. “No go” value is 0.001 in. [0.025 mm] greater in each case.

TABLE 16 Tolerances, Outside Dimensions^A Square and Rectangular Tubing

Largest Nominal Outside Dimension, in. [mm]	Wall Thickness, in. [mm]	Outside Tolerance at All Sides at Corners ± in. [mm]
3/16 to 5/8, incl [5 to 15]	0.020 to 0.083, incl [0.51 to 2.11]	0.004 [0.10]
Over 5/8 to 1 1/8, incl [15 to 30]	0.022 to 0.156, incl [0.56 to 3.96]	0.005 [0.13]
Over 1 1/8 to 1 1/2, incl [30 to 40]	0.025 to 0.192, incl [0.64 to 4.88]	0.006 [0.15]
Over 1 1/2 to 2, incl [40 to 50]	0.032 to 0.192, incl [0.81 to 4.88]	0.008 [0.20]
Over 2 to 3, incl [50 to 75]	0.035 to 0.259, incl [0.89 to 6.58]	0.010 [0.25]
Over 3 to 4, incl [75 to 100]	0.049 to 0.259, incl [1.24 to 6.58]	0.020 [0.51]
Over 4 to 6, incl [100 to 150]	0.065 to 0.259, incl [1.65 to 6.58]	0.020 [0.51]
Over 6 to 8, incl [150 to 200]	0.185 to 0.259, incl [4.70 to 6.58]	0.025 [0.64]

^A Measured at corners at least 2 in. [50 mm] from the cut end of the tubing.

Convexity and concavity: Tubes having two parallel sides are also measured in the center of the flat sides for convexity and concavity. This tolerance applies to the specific size determined at the corners, and is measured on the following basis:

Largest Nominal Outside Dimension, in. [mm]	Tolerance ±, in. [mm]
2 1/2 [65] and under	0.010 [0.25]
Over 2 1/2 to 4 [65 to 100]	0.015 [0.38]
Over 4 to 8 [100 to 200]	0.025 [0.63]

9.5 *Twist*—Twist tolerances are shown in Table 19. The twist in square and rectangular tubing may be measured by holding one end of the tubing on a surface plate and noting the height of either corner of the opposite end of same side above

the surface plate. Twist may also be measured by the use of a beveled protractor equipped with a level, and noting the angular deviation on opposite ends, or at any point throughout the length.

ASTM A513/A513M – 19

TABLE 17 Radii of Corners of Electric-Resistance-Welded Square and Rectangular Tubing^A

Squares and Rectangles Made from Tubes of the Following Diameter Ranges, in. [mm]	Wall Thickness Bwg (in.) [mm]	Radius Tolerances ^B in. [mm]
½ to 1½, incl [15 to 40]	24 (0.022) [0.56]	¼ to ¾ [0.40 to 1.19]
½ to 1½, incl [15 to 40]	22 (0.028) [0.71]	½ to 1/16 [0.79 to 1.59]
½ to 2½, incl [15 to 65]	20 (0.035) [0.89]	½ to 1/16 [0.79 to 1.59]
½ to 2½, incl [15 to 65]	19 (0.042) [1.07]	¾ to 5/64 [1.19 to 1.98]
½ to 4, incl [15 to 100]	18 (0.049) [1.24]	¾ to 5/64 [1.19 to 1.98]
½ to 4½, incl [15 to 105]	16 (0.065) [1.65]	1/16 to 7/64 [1.59 to 2.78]
¾ to 4½, incl [20 to 105]	14 (0.083) [2.11]	5/64 to 1/8 [1.98 to 3.18]
Over 4½ to 6, incl [105 to 150]	14 (0.083) [2.11]	3/16 to 5/16 [4.76 to 7.94]
1 to 4½, incl [25 to 105]	13 (0.095) [2.41]	3/32 to 5/32 [2.38 to 3.97]
Over 4½ to 6, incl [105 to 150]	13 (0.095) [2.41]	3/16 to 5/16 [4.75 to 7.94]
1¼ to 4, incl [30 to 100]	12 (0.109) [2.77]	1/8 to 13/64 [3.18 to 5.16]
Over 4 to 6, incl [100 to 150]	12 (0.109) [2.77]	3/16 to 5/16 [4.76 to 7.94]
1¼ to 4, incl [30 to 100]	11 (0.120) [3.05]	1/8 to 7/32 [3.18 to 5.56]
Over 4 to 6, incl [100 to 150]	11 (0.120) [3.05]	7/32 to 7/16 [5.56 to 11.11]
2 to 4, incl [50 to 100]	10 (0.134) [3.40]	5/32 to 9/32 [3.97 to 7.14]
Over 4 to 6, incl [100 to 150]	10 (0.134) [3.40]	7/32 to 7/16 [5.56 to 11.11]
2 to 4, incl [50 to 100]	9 (0.148) [3.76]	3/16 to 5/16 [4.76 to 7.94]
Over 4 to 8, incl [100 to 200]	9 (0.148) [3.76]	7/32 to 7/16 [5.56 to 11.11]
2 to 8, incl [50 to 200]	8 (0.165) [4.19]	¼ to ½ [6.35 to 12.70]
2 to 8, incl [50 to 200]	7 (0.180) [4.57]	¼ to ½ [6.35 to 12.70]
2½ to 4, incl [65 to 100]	6 (0.203) [5.16]	5/16 to 9/16 [7.93 to 14.29]
Over 4 to 8, incl [100 to 200]	6 (0.203) [5.16]	5/16 to 9/16 [7.93 to 14.29]
2½ to 8, incl [65 to 200]	5 (0.220) [5.59]	3/8 to 5/8 [9.53 to 15.88]
2½ to 8, incl [65 to 200]	4 (0.238) [6.05]	3/8 to 5/8 [9.53 to 15.88]
2½ to 8, incl [65 to 200]	3 (0.259) [6.58]	3/8 to 5/8 [9.53 to 15.88]

^A This table establishes a standard radius. The purchaser and producer may negotiate special radii. Slight radius flattening is more pronounced in heavier wall tubing.
^B These radius tolerances apply to grades of steel covered in Table 1. The purchaser and producer may negotiate tolerances on other grades of steel.

TABLE 18 Length Tolerances—Square and Rectangular Tubing

Lengths, ft. [m]	Tolerances, in. [mm]
1 to 3, incl [0.3 to 1]	±1/16 [1.6]
Over 3 to 12, incl [1 to 4]	±3/32 [2.4]
Over 12 to 20, incl [4 to 6]	±1/8 [3.2]
Over 20 to 30, incl [6 to 9]	±3/16 [4.8]
Over 30 to 40, incl [9 to 12]	±9/16 [9.5]

or octagonal outside, ribbed inside or out, triangular, rounded rectangular and D shapes. Manufacturing practices limit the size range and section available from the various producers. These special sections may be made through turkshead rolls or through a die with or without use of a mandrel. Since the sections are special, dies and other tools are not held available. Therefore, when inquiring for shapes other than square and rectangular, it is essential to give full details as to dimensions and finish.

11. Workmanship, Finish, and Appearance

11.1 The tubing shall be free of injurious defects and shall have a workmanlike finish.

11.2 When burrs must be removed from one or both ends, it shall be specified in the purchase order.

12. Types and Conditions

12.1 The types of tubing covered by this specification are:

Type Number	Code Letters	Description
1a	A.W.H.R.	“as-welded” from hot-rolled steel (with mill scale)
1b	A.W.P.O.	“as-welded” from hot-rolled pickled and oiled steel (mill scale removed)
2	A.W.C.R.	“as-welded” from cold-rolled steel
3	S.D.H.R.	“sink-drawn” hot-rolled steel
4	S.D.C.R.	“sink-drawn,” cold-rolled steel
5	DOM	Drawn Over a Mandrel
6	S.S.I.D.	special smooth inside diameter

12.2 The thermal conditions under which tubing may be furnished are:

9.6 *Straightness*—The straightness tolerance is 1/16 in./3 ft [1.7 mm/1 m]. The test method for straightness measurement is at the manufacturer’s option, unless a specific test method is specified in the purchase order.

10. Tubing Sections Other Than Square and Rectangular

10.1 In addition to square and rectangular tubing, many producers supply a variety of special sections, such as oval, streamlined, hexagonal, octagonal, round inside and hexagonal


A513/A513M – 19

Code	Description
NA	Not Annealed; in the as-welded or as-drawn condition
SRA	Stress Relieved Annealed (at a temperature below the lower critical temperature)
N	Normalized or Annealed (at a temperature above the upper critical temperature)

12.2.1 When the thermal condition is not specified, the tube may be supplied in the NA condition.

12.2.2 When a final thermal treatment is specified, a tight oxide is normal. When an oxide-free surface is specified, the tube may be bright annealed or pickled at the manufacturer's option.

12.3 Flash conditions under which tubing may be furnished are as follows. The flash shall be removed from the outside diameter of tubing covered by this specification. Tubing furnished to this specification may have the following conditions of welding flash on the inside diameter.

12.3.1 *Flash-In*—Tubing in which the inside diameter welding flash does not exceed the wall thickness or $\frac{3}{32}$ in. [2.38 mm], whichever is less. This condition is available in Types 1a, 1b, 2, 3, and 4.

12.3.2 *Flash Controlled to 0.010 in. [0.26 mm], maximum*—Tubing in which the height of the remaining welding flash is controlled so as not to exceed 0.010 in. This condition is available in Types 1a, 1b, and 2 over $1\frac{1}{8}$ -in. [28.5-mm] outside diameter and Types 3 and 4.

12.3.3 *Flash Controlled to 0.005 in. [0.13 mm], maximum*—Tubing produced to outside diameter and wall thickness, inside diameter and wall thickness, or outside diameter and inside diameter tolerances which are so controlled that the height of the remaining inside diameter flash does not exceed 0.005 in. Any remaining inside diameter flash is part of the applicable inside diameter tolerance. This condition is available in Types 1a, 1b, 2, 3, and 4.

12.3.4 *No Flash*—Tubing further processed by DOM for closer tolerances, produced to outside diameter and wall thickness, inside diameter and wall thickness, or outside diameter and inside diameter to tolerances, with no dimensional indication of inside diameter flash, is available in Types 5 and 6.

12.4 Tubes shall be furnished in the following shapes, as specified by the purchaser: round, square, rectangular, or special shapes (as negotiated).

13. Surface Finish

13.1 Tubes shall have a surface finish compatible with the conditions (See Section 12) to which they are ordered (See Appendix X1).

14. Coating

14.1 When specified, tubing shall be coated with a film of oil before shipping to retard rust. Should the order specify that

tubing be shipped without rust retarding oil, the film of oils incidental to manufacture will remain on the surface. If the order specifies no oil, the purchaser assumes responsibility for rust in transit.

14.2 Special surface preparations as may be required for specific applications are not within the scope of this section. Such requirements shall be considered under the supplementary or basis of purchase provisions of this specification and details shall be provided in the purchase order.

15. Rejection

15.1 Tubes that fail to meet the requirements of this specification shall be set aside and the producer shall be notified.

16. Product and Package Marking

16.1 *Civilian Procurement*—Each box, bundle, lift, or piece shall be identified by a tag or stencil with manufacturer's name or brand, specified size, type, purchaser's order number, and this specification number. Bar coding is acceptable as a supplementary identification method. Bar coding should be consistent with the Automotive Industry Action Group [AIAG] standard prepared by the Primary Metals Subcommittee of the AIAG Bar Code Project Team.

16.2 *Government Procurement*—When specified in the contract or order, and for direct procurement by or direct shipment to the Government, marking for shipment, in addition to requirements specified in the contract or order, shall be in accordance with MIL-STD-129 for Military agencies and in accordance with Fed. Std. No. 123 for civil agencies.

16.3 *Bar Coding*—In addition to the requirements in 16.1 and 16.2, bar coding is acceptable as a supplemental identification method. The purchaser may specify in the order a specific bar coding system to be used.

17. Packaging

17.1 *Civilian Procurement*—On tubing 16 gauge, 0.065 in. [1.7 mm] and lighter, the producer will determine whether or not the tubing will be boxed, crated, cartoned, packaged in secured lifts, or bundled to ensure safe delivery unless otherwise instructed. Tubing heavier than 16 gauge will normally be shipped loose, bundled, or in secured lifts. Special packaging requiring extra operations other than those normally used by a producer must be specified on the order.

17.2 *Government Procurement*—When specified in the contract or order, and for direct procurement by or direct shipment to the Government when Section 10, Tubular Products is specified, preservation, packaging, and packing shall be in accordance with the Practices A700.

18. Keywords

18.1 alloy steel tube; carbon steel tube; mechanical tubing; resistance welded steel tube; steel tube; welded steel tube



SUPPLEMENTARY REQUIREMENTS

One or more of the following supplementary requirements may become a part of the specification when specified in the inquiry or invitation to bid, and purchase order or contract. These requirements shall not be considered, unless specified in the order and the necessary tests shall be made at the mill. Mechanical tests shall be performed in accordance with the applicable portions of Test Methods and Definitions **A370**.

S1. Tubes for Cylinders

S1.1 Round tubing, DOM for cylinder applications with inside diameter cleanup allowances is considered to be cylinder tubing. **Table S1.1** shows the minimum inside diameter allowance for removal of inside surface imperfections by a honing operation.

S2. Cleanup by Centerless Grinding

S2.1 Round tubing, DOM for applications with outside diameter allowances is considered to be special smooth outside surface tubing. **Table S2.1** shows the minimum outside diameter stock allowance for removal of outside surface imperfections by centerless grinding.

S3. Cleanup by Machining

S3.1 Cleanup is permitted on round tubing, DOM for applications where machining is required to remove surface imperfections. **Table S3.1** shows the minimum stock allowance for removal of surface imperfections from either or both the outside and inside surfaces by machining.

S4. Special Smooth Inside Surface

S4.1 Round tubing, special smooth inside diameter for cylinder applications with microinch finish and inside diameter cleanup allowances is considered to be special smooth inside surface tubing. **Table S4.1** shows the maximum average microinch readings on the inside surface. **Table S4.2** shows the minimum wall depth allowance for inside surface imperfections.

S5. Hardness and Tensile Requirements

S5.1 When hardness properties are specified on the order, round tubing shall conform to the hardness limits specified in **Table S5.1** unless “Tensile Properties Required” is specified in the purchase order. When “Tensile Properties Required” is specified in the purchase order, round tubing shall conform to the tensile requirements and not necessarily the hardness limits shown in **Table S5.1**. For grades of round tubing not shown in **Table S5.1**, and for all square and rectangular tubing, tensile or hardness limits shall be upon agreement between the manufacturer and the purchaser.

TABLE S1.1 Minimum Inside Diameter Stock Allowance on Diameter^A for Removal of Inside-Surface Imperfections by Honing Operation (DOM Tubing)

Outside Diameter, in. [mm]	Wall Thickness, in., ^B [mm]							
	0.065 [1.65] and under	Over 0.065 [1.65] to 0.125 [31.2], incl	Over 0.125 [31.2] to 0.180 [4.57], incl	Over 0.180 [4.57] to 0.230 [5.84], incl	Over 0.230 [5.84] to 0.360 [9.14], incl	Over 0.360 [9.14] to 0.460 [11.7], incl	Over 0.460 [11.7] to 0.563 [14.3], incl	Over 0.563 [14.3]
Up to and incl 1½ [40]	0.010 [0.25]	0.011 [0.28]	0.013 [0.33]	0.015 [0.38]	0.018 [0.46]
Over 1½ to 3 incl [40 to 75]	0.010 [0.25]	0.012 [0.30]	0.014 [0.36]	0.016 [0.41]	0.018 [0.46]	0.021 [0.53]	0.023 [0.58]	...
Over 3 to 4 incl [75 to 100]	0.011 [0.28]	0.013 [0.33]	0.015 [0.38]	0.017 [0.43]	0.019 [0.48]	0.021 [0.53]	0.023 [0.58]	0.025 [0.64]
Over 4 to 4¾ incl [100 to 120]	...	0.014 [0.36]	0.016 [0.41]	0.018 [0.46]	0.020 [0.51]	0.022 [0.56]	0.024 [0.61]	0.026 [0.66]
Over 4¾ to 6 incl [120 to 150]	...	0.015 [0.38]	0.017 [0.43]	0.019 [0.48]	0.021 [0.53]	0.023 [0.58]	0.025 [0.64]	0.027 [0.69]
Over 6 to 8 incl [150 to 200]	...	0.016 [0.41]	0.018 [0.46]	0.020 [0.51]	0.022 [0.56]	0.024 [0.61]	0.026 [0.66]	0.028 [0.71]
Over 8 to 10½ incl [200 to 265]	0.021 [0.53]	0.023 [0.58]	0.025 [0.64]	0.027 [0.69]	0.029 [0.74]
Over 10½ to 12½ incl [265 to 320]	0.022 [0.56]	0.024 [0.61]	0.026 [0.66]	0.028 [0.71]	0.030 [0.76]
Over 12½ to 14 incl [320 to 355]	0.024 [0.61]	0.025 [0.64]	0.027 [0.69]	0.029 [0.74]	0.031 [0.79]
Over 14 to 15 inc [355 to 380]	0.025 [0.64]	0.026 [0.66]	0.028 [0.71]	0.030 [0.76]	0.032 [0.81]

^A If a specific size is desired, these allowances plus normal size tolerances must be considered in calculating size to be ordered.

^B Where the ellipsis (...) appears in this table, no allowances have been established.

ASTM A513/A513M – 19

TABLE S2.1 Minimum Outside Diameter Stock Allowance on Diameter^A for Removal of Outside-Surface Imperfections by Centerless Grinding (DOM Tubing)

Outside Diameter, in. [mm]	Tubing Wall Thickness, in. [mm] ^B					
	Up to 0.125 [3.2] incl	Over 0.125 [3.2] to 0.180 [4.57] incl	Over 0.180 [4.57] to 0.230 [5.84] incl	Over 0.230 [5.84] to 0.360 [9.14] incl	Over 0.360 [9.14] to 0.460 [11.7] incl	Over 0.460 [11.7]
Up to 3, incl [75]	0.012 [0.30]	0.014 [0.36]	0.016 [0.41]	0.020 [0.51]	0.024 [0.61]	0.026 [0.66]
Over 3 to 4¾, incl [75 to 120]	0.016 [0.41]	0.018 [0.46]	0.020 [0.51]	0.022 [0.56]	0.024 [0.61]	0.026 [0.66]
Over 4¾ to 6, incl [120 to 150]	0.018 [0.46]	0.020 [0.51]	0.022 [0.56]	0.024 [0.61]	0.026 [0.66]	0.028 [0.71]
Over 6 to 7, incl [150 to 180]	0.020 [0.51]	0.022 [0.56]	0.024 [0.61]	0.026 [0.66]	0.028 [0.71]	0.030 [0.76]
Over 7 to 8, incl [180 to 200]	0.026 [0.66]	0.027 [0.69]	0.029 [0.74]	0.031 [0.79]
Over 8 to 10½, incl [200 to 265]	0.027 [0.69]	0.028 [0.71]	0.030 [0.76]	0.032 [0.81]
Over 10½ to 12½, incl [265 to 320]	0.028 [0.71]	0.030 [0.76]	0.032 [0.81]	0.034 [0.85]
Over 12½ to 14 incl [320 to 355]	0.030 [0.76]	0.032 [0.81]	0.034 [0.85]	0.036 [0.91]
Over 14 [355]	0.033 [0.84]	0.035 [0.89]	0.036 [0.91]	0.037 [0.94]

^A If a specific size is desired, these allowances plus normal size tolerances must be considered in calculating size to be ordered.

^B Where the ellipsis (...) appears in this table, no allowances have been established.

TABLE S3.1 Minimum Diameter Stock Allowance for Outside Diameter and Inside Diameter for Removal of Imperfections by Machining (DOM Tubing)^A

NOTE 1—*Camber*—For every foot or fraction thereof over one foot of length, add 0.010 in. [0.25] for camber.

Outside Diameter, in. [mm] ^B	Wall Thickness, in. [mm] ^{B,C}				
	Up to 0.187 [4.75]	Over 0.187 [4.75] to 0.230 [5.84] incl	Over 0.230 [5.84] to 0.360 [9.14] incl	Over 0.360 [9.14] to 0.460 [11.7] incl	Over 0.460 [11.7]
Up to 1½ incl [40]	0.015 [0.38]	0.020 [0.51]	0.025 [0.64]
Over 1½ to 3 incl [40 to 75]	0.020 [0.51]	0.025 [0.64]	0.030 [0.76]	0.030 [0.76]	0.035 [0.89]
Over 3 to 4¾ incl [75 to 120]	0.025 [0.64]	0.030 [0.76]	0.035 [0.89]	0.035 [0.89]	0.040 [1.02]
Over 4¾ to 6 incl [120 to 150]	0.030 [0.76]	0.035 [0.89]	0.040 [1.02]	0.040 [1.02]	0.045 [1.14]
Over 6 to 7 incl [150 to 180]	0.035 [0.89]	0.040 [1.02]	0.045 [1.14]	0.045 [1.14]	0.050 [1.27]
Over 7 to 8 incl [170 to 200]	...	0.045 [1.14]	0.048 [1.22]	0.048 [1.22]	0.053 [1.35]
Over 8 to 10½ incl [200 to 265]	...	0.048 [1.22]	0.050 [1.27]	0.050 [1.27]	0.055 [1.40]
Over 10½ to 15 incl [265 to 380]	...	0.050 [1.27]	0.055 [1.40]	0.055 [1.40]	0.060 [1.52]

^A If a specific size is desired, those allowances plus normal size tolerances must be considered in calculating size to be ordered.

^B Where the ellipsis (...) appears in this table, no allowances have been established.

^C 1 in. = 25.4 mm.

TABLE S4.1 Maximum Average Microinch Readings on Inside Surface (Special Smooth Inside Diameter Tubing)

Outside Diameter, in. [mm]	Tubing Wall Thickness in. [mm] ^A				
	0.065 [1.65] and Under	Over 0.065 [1.65] to 0.150 [3.80], incl	Over 0.150 [3.80] to 0.187 [4.75], incl	Over 0.187 [4.75] to 0.225 [5.72], incl	Over 0.225 [5.72] to 0.312 [7.92], incl
1 to 2½, incl [25 to 65]	40 [0.00101]	45 [0.00114]	50 [0.00127]	55 [0.001397]	70 [0.00178]
Over 2½ to 4½, incl [65 to 115]	40 [0.00101]	50 [0.00127]	60 [0.00152]	70 [0.00178]	80 [0.00203]
Over 4½ to 5½, incl [115 to 140]	...	55 [0.001397]	70 [0.00178]	80 [0.00203]	90 [0.00229]
Over 5½ to 7 incl [140 to 180]	...	55 [0.001397]	70 [0.00178]	80 [0.00203]	90 [0.00229]

^A Where the ellipsis (...) appears in this table, there is no requirement.

S5.2 Number of tests and retests shall be as follows: one tension test per lot shall be made (See Note S1) and 1 % of all tubes per lot but in no case less than 5 tubes shall be tested for hardness. If the results of the mechanical tests do not conform to the requirements shown in the table, retests shall be made on additional tubes double the original number selected, each of which shall conform to the specified requirements.

NOTE S1—A lot shall consist of all tubes, before cutting to length, of the same size and wall thickness which are produced from the same heat of steel and, when heat treated, subjected to the same finishing treatment in a continuous furnace. When final heat treatment is done in a batch-type furnace, the lot shall include all those tubes which are heat treated in the same furnace charge.

S5.3 The yield strength corresponding to a permanent offset of 0.2 % of the gauge length of the specimen or to a total extension of 0.5 % of the gauge length under load shall be determined.

S6. Destructive Weld Tests

S6.1 Round tubing and tubing to be formed into other shapes when in the round form shall meet the following destructive weld tests.

S6.2 *Flattening Test*—A test 4 to 6 in. [100 to 150 mm] in length shall be flattened between parallel plates with the weld 90° from the direction of applied force (at the point of


A513/A513M – 19
TABLE S4.2 Allowance for Surface Imperfections on Inside Diameters of Special Smooth Finish Tubes^A

Outside Diameter Size, in. [mm]	Wall Thickness, in. [mm]	Wall Depth Allowance for Inside Diameter Surface Imperfections, in. [mm]	
		Scores	Pits
Up to 2½ incl [65]	0.065 to 0.109 incl [1.65 to 2.77]	0.001 [0.03]	0.0015 [0.04]
	Over 0.109 to 0.250 incl [2.77 to 6.35]	0.001 [0.03]	0.002 [0.05]
	Over 0.250 to 0.312 incl [6.35 to 7.92]	0.001 [0.03]	0.0025 [0.06]
Over 2½ to 5½ incl [65 to 140]	0.083 to 0.125 incl [2.11 to 3.18]	0.0015 [0.04]	0.0025 [0.06]
	Over 0.125 to 0.187 incl [3.18 to 4.75]	0.0015 [0.04]	0.003 [0.08]
	Over 0.187 to 0.312 incl [4.75 to 7.92]	0.002 [0.05]	0.004 [0.10]
Over 5½ to 7 incl [140 to 180]	0.125 to 0.187 incl [3.18 to 4.75]	0.0025 [0.06]	0.005 [0.13]
	Over 0.187 to 0.312 incl [4.75 to 7.92]	0.003 [0.08]	0.006 [0.15]

^A If a specific size is desired, these allowances plus normal size tolerances must be considered in calculating size to be ordered.

maximum bending) until opposite walls of the tubing meet. Except as allowed in S6.2.1, no opening in the weld shall take place until the distance between the plates is less than two thirds of the original outside diameter of the tubing. No cracks or breaks in the base metal shall occur until the distance between the plates is less than one third of the original outside diameter of the tubing, but in no case less than five times the thickness of the tubing wall. Evidence of lamination or burnt material shall not develop during the flattening process, and the weld shall not show injurious defects.

S6.2.1 When low D-to-t ratio tubing is tested, because the strain imposed due to geometry is unreasonably high on the inside surface at the six and twelve o'clock locations, cracks at these locations shall not be cause for rejection if the D-to-t ratio is less than 10.

S6.3 *Flaring Test*—A section of tube approximately 4 in. [100 mm] in length shall stand being flared with a tool having a 60° included angle until the tube at the mouth of the flare has been expanded 15 % of the inside diameter, without cracking or showing flaws.

S6.4 In order to properly evaluate weld quality, the producer at his option may normalize the test specimen prior to testing.

S6.5 Number of tests and retests:

S6.5.1 Two flattening and two flaring tests shall be made from each lot as specified. Each tested specimen shall conform to the respective requirement (See **Note S1**).

S6.5.2 If the results of the testing do not conform to the requirements, retests shall be made on four additional specimens, each of which shall conform to the respective requirement.

S7. Hydrostatic Test Round Tubing

S7.1 All tubing will be given a hydrostatic test calculated as follows:

$$P = \frac{2St}{D}$$

where:

- P = minimum hydrostatic test pressure, psi or MPa,
- S = allowable fiber stress of 14 000 psi or 96.5 MPa,
- t = specified wall thickness, in. or mm, and
- D = specified outside diameter, in. or mm.

S7.2 The minimum hydrostatic test pressure shall be maintained for not less than 5 s.

S8. Nondestructive Electric Test

S8.1 Each tube shall be tested with a nondestructive electric test in accordance with Practice **E213**, Practice **E273**, Practice **E309**, or Practice **E570**. It is the intent of this test to reject tubes containing injurious defects.

S8.2 For eddy-current testing, the calibration tube shall contain, at the option of the producer, any one of the following discontinuities to establish a minimum sensitivity level for rejection. For welded tubing, they shall be placed in the weld if visible.

S8.2.1 *Drilled Hole*—A hole not larger than 0.031 in. [0.78 mm] in diameter shall be drilled radially and completely through the tube wall, care being taken to avoid distortion of the tube while drilling.

S8.2.2 *Transverse Tangential Notch*—Using a round tool or file with a ¼-in. [6.4-mm] diameter, a notch shall be filed or milled tangential to the surface and transverse to the longitudinal axis of the tube. Said notch shall have a depth not exceeding 12½ % of the specified wall thickness of the tube or 0.004 in. [0.101 mm], whichever is greater.

S8.2.3 *Longitudinal Notch*—A notch 0.031 in. [0.78 mm] or less in width shall be machined in a radial plane parallel to the tube axis on the outside surface of the tube, to have a depth not exceeding 12½ % of the specified wall thickness of the tube or 0.004 in. [0.101 mm], whichever is greater. The length of the notch shall be compatible with the testing method.

S8.3 For ultrasonic testing, the longitudinal calibration reference notches shall be at the option of the producer, any one of the three common notch shapes shown in Practice **E213** or Practice **E273**. The depth of notch shall not exceed 12½ % of the specified wall thickness of the tube or 0.004 in. [0.101 mm], whichever is greater. For welded tubing the notch shall be placed in the weld, if visible.

S8.4 For flux leakage testing, each of the longitudinal calibration notches shall be a straight sided notch not over 12½ % of the wall thickness in depth and not over 1.0 in. [25 mm] in length. Both outside diameter and inside diameter notches shall be placed in the tube located sufficiently apart to enable separation and identification of the signals.

S8.5 Tubing producing a signal equal to or greater than the calibration defect shall be subject to rejection. The area producing the signal may be examined.

 **A513/A513M – 19**

TABLE S5.1 Mechanical Properties for Round Tubing

NOTE 1—These values are based on normal mill stress relieving temperatures. For particular applications, properties may be adjusted by negotiation between purchaser and producer.

NOTE 2—For longitudinal strip tests, the width of the gauge section shall be according to A370 Annex A2, Steel Tubular Products and a deduction of 0.5 percentage points from the basic minimum elongation for each 1/32 in. [0.8 mm] decrease in wall thickness under 5/16 in. [7.9 mm] in wall thickness shall be permitted.

	Yield Strength, ksi [MPa], min	Ultimate Strength, ksi [MPa], min	Elongation in 2 in. [50 mm], %, min	RB min	RB max
As-Welded Tubing					
1008	30 [205]	42 [290]	15	50	
1009	30 [205]	42 [290]	15	50	
1010	32 [220]	45 [310]	15	55	
1015	35 [240]	48 [330]	15	58	
1020	38 [260]	52 [360]	12	62	
1021	40 [275]	54 [370]	12	62	
1025	40 [275]	56 [385]	12	65	
1026	45 [310]	62 [425]	12	68	
1030	45 [310]	62 [425]	10	70	
1035	50 [345]	66 [455]	10	75	
1040	50 [345]	66 [455]	10	75	
1340	55 [380]	72 [495]	10	80	
1524	50 [345]	66 [455]	10	75	
4130	55 [380]	72 [495]	10	80	
4140	70 [485]	90 [620]	10	85	
Normalized Tubing					
1008	23 [160]	38 [260]	30		65
1009	23 [160]	38 [260]	30		65
1010	25 [170]	40 [275]	30		65
1015	30 [205]	45 [310]	30		70
1020	35 [240]	50 [345]	25		75
1021	35 [240]	50 [345]	25		78
1025	37 [255]	55 [379]	25		80
1026	40 [275]	60 [414]	25		85
1030	40 [275]	60 [415]	25		85
1035	45 [310]	65 [450]	20		88
1040	45 [310]	65 [450]	20		90
1340	50 [345]	70 [480]	20		100
1524	45 [310]	65 [450]	20		88
4130	50 [345]	70 [480]	20		100
4140	65 [450]	90 [620]	20		105
Sink-Drawn Tubing					
1008	38 [260]	48 [330]	8	65	
1009	38 [260]	48 [330]	8	65	
1010	40 [275]	50 [345]	8	65	
1015	45 [310]	55 [380]	8	67	
1020	50 [345]	60 [415]	8	70	
1021	52 [360]	62 [425]	7	70	
1025	55 [380]	65 [450]	7	72	
1026	55 [380]	70 [480]	7	77	
1030	62 [425]	70 [480]	7	78	
1035	70 [480]	80 [550]	7	82	
DOM Tubing					
1008	50 [345]	60 [415]	5	73	
1009	50 [345]	60 [415]	5	73	
1010	50 [345]	60 [415]	5	73	
1015	55 [380]	65 [450]	5	77	
1020	60 [415]	70 [480]	5	80	
1021	62 [425]	72 [495]	5	80	
1025	65 [450]	75 [515]	5	82	
1026	70 [480]	80 [550]	5	85	
1030	75 [515]	85 [585]	5	87	
1035	80 [550]	90 [620]	5	90	
1040	80 [550]	90 [620]	5	90	
1340	85 [585]	95 [655]	5	90	
1524	80 [550]	90 [620]	5	90	
4130	85 [585]	95 [655]	5	90	
4140	100 [690]	110 [760]	5	90	
DOM Stress-Relieved Tubing					
1008	45 [310]	55 [380]	12	68	
1009	45 [310]	55 [380]	12	68	
1010	45 [310]	55 [380]	12	68	
1015	50 [345]	60 [415]	12	72	


A513/A513M – 19
TABLE *Continued*

	Yield Strength, ksi [MPa], min	Ultimate Strength, ksi [MPa], min	Elongation in 2 in. [50 mm], %, min	RB min	RB max
1020	55 [380]	65 [450]	10	75	
1021	58 [400]	68 [470]	10	75	
1025	60 [415]	70 [480]	10	77	
1026	65 [450]	75 [515]	10	80	
1030	70 [480]	80 [550]	10	81	
1035	75 [515]	85 [585]	10	85	
1040	75 [515]	85 [585]	10	85	
1340	80 [550]	90 [620]	10	87	
1524	75 [515]	85 [585]	10	85	
4130	80 [550]	90 [620]	10	87	
4140	95 [655]	105 [725]	10	90	

S8.5.1 Test signals produced by imperfections which cannot be identified, or produced by cracks or crack-like defects shall result in rejection of the tube subject to rework and retest.

S8.5.2 Test signals produced by imperfections such as those listed below may be judged as injurious or noninjurious depending on visual observation of their severity or the type of signal they produce on the testing equipment used, or both:

S8.5.2.1 Dings,

S8.5.2.2 Straightener marks,

S8.5.2.3 Loose inside diameter bead and cutting chips,

S8.5.2.4 Scratches,

S8.5.2.5 Steel die stamps,

S8.5.2.6 Chattered flash trim,

S8.5.2.7 Stop marks, or

S8.5.2.8 Tube reducer ripple.

S8.5.3 Any imperfection of the above type exceeding 0.004 in. [0.101 mm] or 12½% of the specified wall thickness (whichever is greater) in depth shall be considered injurious.

S8.5.3.1 If the imperfection is judged as injurious, the tubes shall be rejected but may be reconditioned and retested providing the dimensional requirements are met.

S8.5.3.2 If the imperfection is explored to the extent that it can be identified as noninjurious, the tubes may be accepted without further test providing the imperfection does not encroach on the minimum wall thickness, after due allowance for cleanup in mandrel drawn tubes.

S9. Certification for Government Orders

S9.1 A producer's or supplier's certification shall be furnished to the Government that the material was manufactured, sampled, tested, and inspected in accordance with this specification and has been found to meet the requirements. This certificate shall include a report of heat analysis (product analysis when requested in the purchase order), and when specified in the purchase order or contract, a report of test results shall be furnished.

S10. Rejection Provisions for Government Orders

S10.1 Each length of tubing received from the manufacturer may be inspected by the purchaser and, if it does not meet the requirements of the specification based on the inspection and test method as outlined in the specification, the tube may be rejected and the manufacturer shall be notified. Disposition of rejected tubing shall be a matter of agreement between the manufacturer and the purchaser.

S10.2 Material that fails in any of the forming operations or in the process of installation and is found to be defective shall be set aside and the manufacturer shall be notified for mutual evaluation of the material's suitability. Disposition of such material shall be a matter for agreement.

APPENDIX

(Nonmandatory Information)

X1. MEASURING MICROINCH FINISH

X1.1 The procedure for making microinch readings on interior surfaces of cold worked tubing (not polished or ground) ½-in. [12.7-mm] inside diameter and larger is as follows:

X1.1.1 Measurements on tubing with longitudinal or no predominant lay should be circumferential on the inside surface of the straight tube, prior to any fabrication, on a plane

approximately perpendicular to the tube axis. Measurements on tubing with circumferential lay should be longitudinal.

X1.1.2 Measurements should be made not less than 1 in. [25.4 mm] from the end.

X1.1.3 Measurements should be made at four positions approximately 90° apart or over a complete circumference if the trace should otherwise overlap.


A513/A513M – 19

X1.1.4 The length of trace should be in accordance with the latest revision of Section 4.5 of ASME B46.1 (not less than 0.600 in. [15.24 mm] long).

X1.1.5 A minimum of three such measurements should be made spaced not less than ¼ in. [6.4 mm] apart along the longitudinal axis.

X1.1.6 The numerical rating shall be the arithmetical average microinch of all readings taken. Each reading to be averaged should be the mean position of the indicator during the trace; any momentary meter excursions occupying less than 10 % of the total trace should be ignored.

X1.1.7 A deviation in numerical rating in various parts of a tube may be expected. Experience to date indicates that a variation of about ±35 % is normal.

X1.2 Instruments should meet the specifications given in the latest revision of ASME B46.1.

X1.3 Mechanical tracing is preferred. If hand tracing is used, the speed of trace should not vary by more than ±20 % from the required to give the appropriate cutoff. The 0.030-in. [0.76 mm] roughness width cutoff should be used.

X1.4 Microinch [0.0000254 mm] determinations only refer to roughness of areas that do not contain a defect, injurious or otherwise. Such defects as seams, slivers, pits, laps, etc., are subject to ordinary visual inspection in accordance with applicable specifications or trade customs, and have no relationship to roughness.

SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this specification since the last issue, A513/A513M – 18, that may impact the use of this specification. (Approved March 1, 2019)

(I) Corrected seven conversion errors in **Table 10**. 0.109 in. was incorrectly identified as 1.77 mm.

Committee A01 has identified the location of selected changes to this specification since the last issue, A513 – 15, that may impact the use of this specification. (Approved Sept. 1, 2018)

(I) Revised **7.2** to allow spectrochemical analysis per Practice **A751**.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/